

22 MARCH 2021

NEAR-SURFACE MINERALISATION AT RASKA CONTINUES TO GROW & DEPLOYMENT OF THIRD RIG FOR REGIONAL BROWNFIELD EXPLORATION

ABOUT ADRIATIC METALS (ASX:ADT, LSE:ADT1)

Adriatic Metals Plc is focused on the development of the 100%-owned, Vares high-grade silver project in Bosnia & Herzegovina, and exploration at the Raska base & precious metals project in Serbia.

DIRECTORS

Mr Michael Rawlinson
NON-EXECUTIVE CHAIRMAN

Mr Paul Cronin
MANAGING DIRECTOR & CEO

Mr Peter Bilbe
NON-EXECUTIVE DIRECTOR

Mr Julian Barnes
NON-EXECUTIVE DIRECTOR

Ms Sandra Bates
NON-EXECUTIVE DIRECTOR

Ms Sanela Karic
NON-EXECUTIVE DIRECTOR

adriaticmetals.com

RASKA PROJECT EXPLORATION HIGHLIGHTS

Kizevak Prospect

Exploration drilling continues at Kizevak with near-surface, high grade mineralisation identified in KZDD-051, located up-dip from a thick, deeper lens:

- 15.0 metres at 2.5 % zinc, 1.7 % lead, 26 g/t silver, 0.3 g/t gold (4.6% ZnEq) from 7.0 metres, including
 - 6.1 metres at 4.6 % zinc, 3.4 % lead, 41 g/t silver, 0.5 g/t gold (8.2% ZnEq) from 9.9 metres

KZDD-042 has extended mineralisation down dip and southeast from historically defined limits of mineralisation, which remains open:

- 10.2 metres at 2.1 % zinc, 1.0 % lead, 12 g/t silver, 0.4 g/t gold (3.5% ZnEq) from 70.8 metres, including
 - 4.3 metres at 3.3 % zinc, 1.6 % lead, 22 g/t silver, 0.6 g/t gold (5.6% ZnEq) from 71.7 metres

Sastavci Prospect

SSDD-006 intercepted two thick zones of mineralisation that are both sub-parallel to the historically mined vein zone and are open to the northwest:

- 15.8 metres at 3.8 % zinc, 1.5 % lead, 28 g/t silver and 0.2 g/t gold (5.2% ZnEq) from 122.5 metres, including
 - 8.8 metres at 6.5 % zinc, 2.6 % lead, 48 g/t silver and 0.2 g/t gold (8.9% ZnEq) from 129.5 metres
- 13.3 metres at 1.3 % zinc, 0.7 % lead, 9 g/t silver and 0.3 g/t gold (2.4% ZnEq) from 153.7 metres

SSDD-007 intercepted a broad, well mineralised zone from surface which continues to demonstrate that much thicker zones of mineralisation are present than historically interpreted:

- 36.0 metres at 3.7 % zinc, 1.4 % lead, 21 g/t silver and 0.2 g/t gold (4.9% ZnEq) from surface, including
 - 8.4 metres at 8.1 % zinc, 1.9 % lead, 30 g/t silver and 0.3 g/t gold (9.4% ZnEq) from 4.6 metres, and
 - 8.0 metres at 6.3 % zinc, 3.1 % lead, 49 g/t silver and 0.2 g/t gold (9.0% ZnEq) from 21.3 metres

DEPLOYMENT OF THIRD DIAMOND DRILL RIG

As part of the 25,000 metres of diamond drilling planned at the Raska Project for 2021, a third drill rig will be deployed to focus on regional exploration.



Adriatic Metals PLC (ASX:ADT, LSE:ADT1) ("Adriatic" or the "Company") is pleased to report on recent exploration results, as well as an expansion of the Company's exploration plans at the Raska Project in Serbia.

Raska Exploration Results

Kizevak continues to deliver significant drill results, expanding and confirming the previously known mineralised zones, and demonstrating good continuity of the mineralisation. Further drilling at Kizevak will continue to focus on exploration along strike and of down dip extensions.

Drilling at Sastavci continues to define thick mineralised zones at the base of the historic open pit, as well as the presence of several sub-parallel vein zones outside of the pit limits. A further 4,000 metres of drilling is planned at Sastavci to step out along strike of the two main zones of mineralisation identified to date, as well as explore nearby sub-parallel structures identified from mapping, soil geochemistry and 3D magnetic data interpretation.

A diamond drill rig is onsite at each of the Kizevak and Sastavci prospects.

Expanded Exploration Program at Raska

The Company has expanded its exploration plans in Serbia, with 25,000 m of exploration drilling budgeted across the Raska Project for 2021. The program will continue the Company's primary focus of delineating near-surface resources amenable to low cost, open-pit mining at Kizevak and Sastavci. In addition, the Company will commence a new program designed to step-out and identify new areas of base and precious metal mineralisation from brownfield targets across the wider licence area. A third diamond drill rig will be deployed to the Raska Project within the next month, which will be dedicated to this new brownfields exploration program.

Following the analysis of historical and recently acquired data, the brownfields exploration program will initially target the Karadak and Rudnica epithermal vein prospects. Drilling will start with a 2,200 metre program designed to test the Karadak prospect, which is a near-surface vein-type prospect with a historical, non-compliant Mineral Resource. In addition, a 1,500 metre program is planned to follow up on the polymetallic vein intercepts at the Rudnica prospect, which is a copper-gold prospect cross cut by later base and precious metal epithermal veins.

Paul Cronin, Adriatic's Managing Director and CEO, commented: *"Our geological understanding of the Raska Project continues to evolve following the discovery of further sub-parallel vein zones at both Kizevak and Sastavci. The exploration work completed to date has demonstrated that there remains an incredible amount of potential across, not only these two prospects, but the wider project area.*

Adriatic will continue to systematically explore around the Kizevak and Sastavci prospects, with the aim to generating a sizeable resource to support a significant open-pit mining operation. Based on the results to date a maiden resource and scoping study at Raska will be delivered in the 2nd half of the year, once the DFS, ESIA and the project financing workstreams at Vares have been completed and construction is underway.

In addition, I am incredibly excited about the regional prospectivity of the wider Raska Project, which following an extensive review of historical data, is increasing in focus. We have identified a number of drill ready targets, which will be drilled following the deployment of the third rig, expected imminently. "



KIZEVAK DRILLING RESULTS

KZDD-051, which is located southeast of the historic open pit, has returned significant mineralised intercepts near surface. The results from this drill hole give further confirmation that moderate to high-grade mineralisation is present from surface, with mineralisation demonstrated to be continuous to at least 250 m down dip. See Figures 2 and 3.

This same lens has been further extended to the southeast with drill hole KZDD-042, where mineralisation was intercepted outside of the extents of the historic drilling and remains open. See Figure 3.

Significant results for the other drill holes from the 2020 drilling campaign, are in Appendix 1, Table 1. The 2020 drilling demonstrated that mineralisation is present in a continuous mineralised corridor, with thick (up to 50m) vein zones, which are consistently intercepted over a 900 m strike length. Mineralisation remains open to the northwest, as well as along strike, from several sub-parallel vein zones that currently remain unexplored.

SASTAVCI DRILLING RESULTS

Exploration drilling at Sastavci continues to demonstrate the presence of numerous sub-parallel polymetallic veins, which occur from surface. The intercepts in SSDD-006 are located outside of the historic pit limits and 80 metres northwest of similar intercepts in SSDD-004. These zones remain open along strike to the northwest and are untested by historic or recent drilling, representing a significant exploration target. See Figures 4 and 5

Results from drill hole SSDD-007 are further evidence of a thick vein zone at the base of the historic open pit, with coherent structurally-controlled, high-grade portions. SSDD-007 also intercepted several sub-parallel veins southeast of this main zone with variable grade and width. These additional mineralised veins were not historically mined and represent an opportunity to further expand on the current known mineralised footprint at Sastavci. See Figures 4 and 6.




Figure 1: Plan view map of the Raska Project permit area, which include the Kizevak and Sastavci prospects, which are contiguous to past-producing open pit mines of their respective name




Figure 2: Plan view map of the Kizevak prospect showing both historic exploration drilling and adits, as well as recent Adriatic drilling. The historic Kizevak open pit is visible to the northwest, and mineralisation extending to the southeast and northwest is entirely open.




Figure 3: Cross-section (A'-A) through the Kizevak deposit (KZDD-051).




Figure 4: Plan view map of the Sastavci prospect showing historic drilling and adits, including highlighted results from recent drilling and the northern gold in soil anomaly.




Figure 5: Cross-section (B'-B) through the Sastavci deposit (SSDD-006).




Figure 6: Cross-section (C'-C) through the Sastavci deposit (SSDD-007).



Authorised by, and for further information please contact, Paul Cronin
Managing Director & CEO
info@adriaticmetals.com

-ends-

MARKET ABUSE REGULATION DISCLOSURE

The information contained within this announcement is deemed by the Company (LEI: 549300OHAH2GL1DP0L61) to constitute inside information as stipulated under the Market Abuse Regulations (EU) No. 596/2014. The person responsible for arranging and authorising the release of this announcement on behalf of the Company is Paul Cronin, Managing Director and CEO.

For further information please visit www.adriaticmetals.com, [@AdriaticMetals](https://twitter.com/AdriaticMetals) on Twitter, or contact:

Adriatic Metals PLC

Paul Cronin / Thomas Horton

Tel: +44 (0) 7866 913207

Tavistock Communications Limited

Charles Vivian

Tel: +44 (0) 7977 297903

Edward Lee

Tel: +44 (0) 7736 220565

Gareth Tredway

Tel: +44 (0) 7785 974264

The Capital Network

Julia Maguire/Lelde Smits

Tel: +61 2 8999 3699

COMPETENT PERSONS REPORT

The information in this report which relates to exploration results is based on information compiled by Mr Phillip Fox, who is a member of the Australian Institute of Geoscientists (AIG). Mr Fox is a consultant to Adriatic Metals PLC, and has sufficient experience relevant to the style of mineralisation and type of deposit under consideration and to the activity he is undertaking to qualify as a Competent Person as defined in the 2012 Edition of the "Australian Code of Reporting of Exploration Results, Mineral Resources and Ore Reserves". Mr Fox consents to the inclusion in this report of the matters based on that information in the form and context in which it appears.

ABOUT ADRIATIC METALS

Adriatic Metals Plc (ASX:ADT, LSE:ADT1) is a precious and base metals explorer and developer that owns the world-class Vares Silver Project in Bosnia & Herzegovina and the Raska Project in Serbia.

The Vares project's captivating economics and impressive resource inventory have attracted Adriatic's highly experienced team, which is expediting exploration efforts to expand the current JORC resource. Results of a recent pre-feasibility study announced on 15 October 2020 indicate a post-tax NPV8% of US\$1,040 million and IRR of 113%. Leveraging its first-mover advantage, Adriatic is rapidly advancing the project into the development phase and through to production with significant cornerstone investment of US\$28 million from Queen's Road Capital Investment and EBRD.

There have been no material changes to the assumptions underpinning the forecast financial information derived from the production target in the 15 October 2020 announcement and these assumptions continue to apply. There have been no material changes to the assumptions and technical parameters on the updated Mineral Resource Estimate announced on 1 September 2020 and these assumptions continue to apply.



Adriatic Metals acquired TSX-listed Tethyan Resource Corp in 2020, to advance the former Kizevak and Sastavci polymetallic mines in the Raska District, southern Serbia.

DISCLAIMER

Forward-looking statements are statements that are not historical facts. Words such as "expect(s)", "feel(s)", "believe(s)", "will", "may", "anticipate(s)", "potential(s)" and similar expressions are intended to identify forward-looking statements. These statements include, but are not limited to statements regarding future production, resources or reserves and exploration results. All of such statements are subject to certain risks and uncertainties, many of which are difficult to predict and generally beyond the control of the Company, that could cause actual results to differ materially from those expressed in, or implied or projected by, the forward-looking information and statements. These risks and uncertainties include, but are not limited to: (i) those relating to the interpretation of drill results, the geology, grade and continuity of mineral deposits and conclusions of economic evaluations, (ii) risks relating to possible variations in reserves, grade, planned mining dilution and ore loss, or recovery rates and changes in project parameters as plans continue to be refined, (iii) the potential for delays in exploration or development activities or the completion of feasibility studies, (iv) risks related to commodity price and foreign exchange rate fluctuations, (v) risks related to failure to obtain adequate financing on a timely basis and on acceptable terms or delays in obtaining governmental approvals or in the completion of development or construction activities, and (vi) other risks and uncertainties related to the Company's prospects, properties and business strategy. Our audience is cautioned not to place undue reliance on these forward-looking statements that speak only as of the date hereof, and we do not undertake any obligation to revise and disseminate forward-looking statements to reflect events or circumstances after the date hereof, or to reflect the occurrence of or non-occurrence of any events.



APPENDIX 1- ASSAY TABLES

Table 1– Significant intercepts for reported drill holes

Hole ID	From (m)	To (m)	Interval (m)	ZnEq (%)	Zn (%)	Pb (%)	Ag (g/t)	Au (g/t)	Pb+Zn (%)
KZDD-040	193.4	200.7	7.3	1.1	0.1	0.1	2.0	0.4	0.2
KZDD-041	13.0	20.2	7.2	1.1	0.8	0.3	1.6	0.1	1.1
	54.0	70.0	16.0	1.3	0.8	0.4	3.1	0.1	1.2
KZDD-042	70.8	81.0	10.2	3.5	2.1	1.0	12.4	0.4	3.2
including	71.7	76.0	4.3	5.6	3.3	1.6	22.3	0.6	4.9
	94.0	102.0	8.0	1.9	1.4	0.6	6.6	0.1	2.0
KZDD-043	16.0	26.0	10.0	1.4	0.6	0.6	8.0	0.1	1.3
	38.6	42.6	4.0	2.3	1.4	1.0	10.5	0.1	2.4
	115.0	126.0	11.0	1.7	1.0	0.3	4.0	0.3	1.3
KZDD-045	226.7	230.0	3.3	1.8	1.1	0.6	6.5	0.2	1.7
KZDD-046	183.0	186.0	3.0	1.2	0.7	0.3	6.7	0.1	1.0
KZDD-047	14.3	19.8	5.5	2.6	1.7	0.9	9.1	0.1	2.6
	238.0	245.0	7.0	1.6	0.7	0.5	4.9	0.3	1.2
KZDD-048	29.0	44.0	15.0	1.9	1.4	0.7	7.0	0.1	2.1
including	32.0	34.7	2.7	4.8	3.4	1.6	22.3	0.1	5.0
KZDD-049	23.0	43.0	20.0	1.3	1.1	0.3	2.8	0.0	1.5
KZDD-051	7.0	22.0	15.0	4.6	2.5	1.7	25.8	0.3	4.2
including	9.9	16.0	6.1	8.2	4.6	3.4	41.2	0.5	8.0
	41.0	60.0	19.0	2.6	1.9	0.9	10.1	0.1	2.8
including	57.0	60.0	3.0	10.1	7.7	3.3	43.0	0.2	10.9
SSDD-006	70.0	73.5	3.5	3.1	1.9	1.1	23.7	0.1	3.0
	122.5	138.3	15.8	5.2	3.8	1.5	28.1	0.2	5.4
including	129.5	138.3	8.8	8.9	6.5	2.6	47.7	0.2	9.1
	153.7	167.0	13.3	2.4	1.3	0.7	9.0	0.3	2.0
	239.0	243.3	4.3	4.8	2.6	1.0	30.2	0.6	3.6
SSDD-007	0.0	36.0	36.0	4.9	3.7	1.4	21.2	0.2	5.1
including	4.6	13.0	8.4	9.4	8.1	1.9	30.0	0.3	10.0
and	21.3	29.3	8.0	9.0	6.3	3.1	48.9	0.2	9.4
	63.3	64.7	1.4	14.2	9.3	4.5	90.6	0.6	13.8
	145.0	147.2	2.2	11.6	6.7	5.2	91.2	0.1	11.9
	189.5	224.0	34.5	2.0	0.8	0.6	11.9	0.3	1.4
	242.0	259.0	17.0	2.3	0.5	0.5	14.2	0.6	1.0
	274.1	279.0	4.9	3.0	0.4	1.5	39.5	0.4	1.9
Notes 1. Significant intervals are estimated using a 1% Pb+Zn cut off and 5 metres consecutive internal dilution. 2. ZnEq grades are based on the following metal prices: \$1850/oz gold, \$22/oz silver, \$1900/t lead, \$2350/t zinc. 3. The following metal recoveries were derived from preliminary testing: 75% silver, 85% lead and 85 % zinc. Gold recovery of 80% was estimated as there have been no gold recovery tests conducted to date. 4. A 100% payability was assumed for each metal and requires further investigation. 5. The zinc equivalent calculation is as follows: $ZnEq = 100 * ((Au \text{ grade g/t} / 31.103 * Au \text{ recovery \%} * Au \text{ price \$ / oz}) + (Ag \text{ grade g/t} / 31.103 * Ag \text{ recovery \%} * Ag \text{ price \$ / oz}) + (Pb \text{ grade \%} / 100 * Pb \text{ recovery \%} * Pb \text{ price \$ / t}) + (Zn \text{ grade \%} / 100 * Zn \text{ recovery \%} * Zn \text{ price \$ / t})) / Zn \text{ price \$ / t}$									

**Table 2 – Collar information for reported drill holes**

Hole ID	Easting (m)	Northing (m)	Elevation (m)	Depth (m)	Azimuth (°)	Inclination (°)
KZDD-040	476215.594	4792852.417	816.25	252	200.3	-55.4
KZDD-041	476060.981	4792845.407	762.186	151	213.7	-55.05
KZDD-042	475853.06	4792977.36	723.213	155.9	211.2	-80.4
KZDD-043	476419.993	4792652.822	885.508	353	204.08	-55.41
KZDD-045	476259.685	4792821.095	829.436	296.6	222.7	-50.1
KZDD-046	475833.686	4793087.614	737.608	257.7	212	-79.3
KZDD-047	476302.328	4792786.438	837.64	300	211.8	-55.2
KZDD-048	475897.818	4792942.045	728.973	269.6	188.58	-55.58
KZDD-049	475895.571	4792941.54	729.082	150.7	219.33	-56.19
KZDD-051	475709.99	4792918.01	728.45	98.4	213.9	-55.7
SSDD-006	476720.717	4796628.309	1001.387	326.6	35.4	-55.6
SSDD-007	476772.74	4796553.429	987.149	365.7	31.9	-56.1

Note: Coordinates are shown using the UTM WGS84 projection, Zone 34 Northern Hemisphere

Table 3 – Assay data for reported drill holes

Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-040	0	105	105	Not sampled				
KZDD-040	105	107	2	0.011	<0.005	<1	0.006	0.0135
KZDD-040	107	109	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-040	109	111	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-040	111	113	2	0.01	<0.005	<1	0.018	0.0125
KZDD-040	113	115	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-040	115	115.8	0.8	0.011	0.009	<1	<0.005	0.02
KZDD-040	115.8	116.3	0.5	0.013	0.011	<1	0.047	0.024
KZDD-040	116.3	117.3	1	0.017	0.012	<1	0.053	0.029
KZDD-040	117.3	118	0.7	0.018	0.012	<1	0.022	0.03
KZDD-040	118	118.9	0.9	0.032	0.015	<1	0.007	0.047
KZDD-040	118.9	119.4	0.5	0.155	0.029	<1	0.033	0.184
KZDD-040	119.4	121	1.6	0.015	0.005	<1	<0.005	0.02
KZDD-040	121	123	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-040	123	125	2	0.011	0.007	<1	<0.005	0.018
KZDD-040	125	126	1	0.12	0.067	1	0.028	0.187
KZDD-040	126	128	2	0.01	<0.005	<1	0.007	0.0125
KZDD-040	128	130	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-040	130	131.5	1.5	0.011	<0.005	<1	0.006	0.0135
KZDD-040	131.5	132.2	0.7	0.59	0.806	2	0.005	1.396
KZDD-040	132.2	134	1.8	0.064	0.037	<1	0.005	0.101
KZDD-040	134	136	2	0.013	<0.005	<1	0.009	0.0155
KZDD-040	136	137	1	0.955	0.103	<1	0.054	1.058
KZDD-040	137	138.3	1.3	0.016	<0.005	<1	<0.005	0.0185
KZDD-040	138.3	140	1.7	0.009	<0.005	<1	<0.005	0.0115
KZDD-040	140	142	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-040	142	144	2	0.018	0.007	<1	<0.005	0.025
KZDD-040	144	146	2	0.017	<0.005	<1	<0.005	0.0195
KZDD-040	146	148	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-040	148	148.8	0.8	0.01	<0.005	<1	<0.005	0.0125
KZDD-040	148.8	149.7	0.9	0.249	0.043	<1	0.013	0.292
KZDD-040	149.7	151	1.3	0.007	<0.005	<1	<0.005	0.0095
KZDD-040	151	153	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-040	153	155	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-040	155	157	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-040	157	159	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-040	159	161	2	0.009	<0.005	<1	<0.005	0.0115



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-040	161	163	2	0.028	0.019	<1	0.013	0.047
KZDD-040	163	165	2	0.035	0.025	<1	0.019	0.06
KZDD-040	165	167	2	0.015	<0.005	<1	<0.005	0.0175
KZDD-040	167	169	2	0.014	<0.005	<1	<0.005	0.0165
KZDD-040	169	171	2	0.014	<0.005	<1	0.007	0.0165
KZDD-040	171	173	2	0.014	0.006	<1	0.005	0.02
KZDD-040	173	174	1	0.066	0.096	<1	0.048	0.162
KZDD-040	174	176	2	0.011	<0.005	1	0.014	0.0135
KZDD-040	176	178	2	0.006	<0.005	1	0.006	0.0085
KZDD-040	178	180	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-040	180	182	2	<0.005	<0.005	<1	<0.005	0.0065
KZDD-040	182	184	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-040	184	186	2	<0.005	<0.005	1	<0.005	0.0065
KZDD-040	186	188	2	0.013	<0.005	<1	<0.005	0.0155
KZDD-040	188	189	1	0.016	0.012	<1	0.016	0.028
KZDD-040	189	189.7	0.7	0.038	0.099	<1	0.268	0.137
KZDD-040	189.7	190.2	0.5	0.111	0.113	1	0.121	0.224
KZDD-040	190.2	192	1.8	0.014	<0.005	<1	0.005	0.0165
KZDD-040	192	192.8	0.8	0.036	0.018	<1	0.017	0.054
KZDD-040	192.8	193.4	0.6	0.17	0.112	4	0.176	0.282
KZDD-040	193.4	194	0.6	0.112	0.109	1	0.305	0.221
KZDD-040	194	194.5	0.5	0.017	0.012	<1	0.066	0.029
KZDD-040	194.5	195.3	0.8	0.175	0.119	1	0.638	0.294
KZDD-040	195.3	196	0.7	0.083	0.161	2	0.265	0.244
KZDD-040	196	196.5	0.5	0.041	0.083	3	0.081	0.124
KZDD-040	196.5	197.2	0.7	0.055	0.035	<1	0.234	0.09
KZDD-040	197.2	198	0.8	0.244	0.147	3	0.709	0.391
KZDD-040	198	198.6	0.6	0.436	0.095	3	0.69	0.531
KZDD-040	198.6	199.5	0.9	0.172	0.129	2	0.06	0.301
KZDD-040	199.5	200.2	0.7	0.062	0.126	4	0.915	0.188
KZDD-040	200.2	200.7	0.5	0.055	0.06	2	0.768	0.115
KZDD-040	200.7	202.5	1.8	0.005	<0.005	1	0.007	0.0075
KZDD-040	202.5	204	1.5	0.005	<0.005	<1	0.009	0.0075
KZDD-040	204	205	1	0.027	0.013	<1	<0.005	0.04
KZDD-040	205	207	2	0.016	<0.005	<1	0.006	0.0185
KZDD-040	207	208.4	1.4	0.058	0.035	<1	0.035	0.093
KZDD-040	208.4	209.3	0.9	0.574	0.373	2	0.105	0.947
KZDD-040	209.3	209.9	0.6	0.079	0.021	1	0.101	0.1
KZDD-040	209.9	210.5	0.6	0.099	0.045	<1	0.068	0.144
KZDD-040	210.5	212	1.5	0.008	<0.005	<1	0.005	0.0105
KZDD-040	212	214	2	0.024	<0.005	<1	0.006	0.0265
KZDD-040	214	216	2	0.012	<0.005	<1	0.009	0.0145
KZDD-040	216	218	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-040	218	220	2	0.006	<0.005	<1	0.009	0.0085
KZDD-040	220	222	2	0.007	<0.005	<1	0.005	0.0095
KZDD-040	222	252	30	Not sampled				
KZDD-041	0	3	3	0.315	0.02	<1	0.017	0.335
KZDD-041	3	4	1	0.054	0.006	<1	0.009	0.06
KZDD-041	4	5	1	0.028	0.013	<1	0.026	0.041
KZDD-041	5	6	1	0.124	0.057	<1	0.024	0.181
KZDD-041	6	7	1	0.018	<0.005	<1	0.006	0.0205
KZDD-041	7	9	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-041	9	11	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-041	11	13	2	0.018	0.007	<1	0.017	0.025
KZDD-041	13	14	1	0.796	0.372	1	0.064	1.168
KZDD-041	14	14.6	0.6	0.345	0.176	<1	0.052	0.521



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-041	14.6	15.1	0.5	0.582	0.348	2	0.087	0.93
KZDD-041	15.1	16	0.9	0.078	0.047	<1	0.031	0.125
KZDD-041	16	17	1	0.349	0.167	<1	0.074	0.516
KZDD-041	17	18	1	1.545	0.589	3	0.096	2.134
KZDD-041	18	19	1	0.301	0.157	2	0.033	0.458
KZDD-041	19	19.6	0.6	2.83	0.722	3	0.075	3.552
KZDD-041	19.6	20.2	0.6	0.867	0.341	2	0.082	1.208
KZDD-041	20.2	21	0.8	0.305	0.193	1	0.038	0.498
KZDD-041	21	22	1	0.03	0.021	<1	0.013	0.051
KZDD-041	22	23.2	1.2	0.068	0.017	1	0.009	0.085
KZDD-041	23.2	25	1.8	0.01	0.005	<1	0.009	0.015
KZDD-041	25	27	2	0.088	0.058	<1	0.01	0.146
KZDD-041	27	28	1	0.022	0.015	<1	0.017	0.037
KZDD-041	28	30	2	0.024	0.01	1	0.016	0.034
KZDD-041	30	32	2	0.01	<0.005	<1	0.009	0.0125
KZDD-041	32	33	1	0.019	0.01	<1	0.031	0.029
KZDD-041	33	34	1	0.009	<0.005	<1	0.04	0.0115
KZDD-041	34	35	1	0.224	0.137	2	0.034	0.361
KZDD-041	35	36	1	0.039	0.025	<1	0.007	0.064
KZDD-041	36	38	2	0.058	0.034	<1	0.017	0.092
KZDD-041	38	40	2	0.02	<0.005	1	0.015	0.0225
KZDD-041	40	41	1	0.869	0.268	1	0.1	1.137
KZDD-041	41	42	1	0.257	0.085	<1	0.064	0.342
KZDD-041	42	43	1	0.027	0.016	<1	0.027	0.043
KZDD-041	43	45	2	0.019	<0.005	<1	0.005	0.0215
KZDD-041	45	47	2	0.019	<0.005	2	0.005	0.0215
KZDD-041	47	49	2	0.006	<0.005	<1	0.012	0.0085
KZDD-041	49	51	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-041	51	53	2	0.015	<0.005	<1	<0.005	0.0175
KZDD-041	53	54	1	0.101	0.022	<1	0.014	0.123
KZDD-041	54	55	1	0.966	0.32	8	0.242	1.286
KZDD-041	55	55.7	0.7	0.457	0.228	1	0.301	0.685
KZDD-041	55.7	56.4	0.7	0.391	0.193	<1	0.178	0.584
KZDD-041	56.4	57	0.6	3.57	1.475	8	0.249	5.045
KZDD-041	57	58	1	1.02	0.298	2	0.248	1.318
KZDD-041	58	59	1	0.91	0.422	2	0.101	1.332
KZDD-041	59	60	1	0.341	0.145	1	0.058	0.486
KZDD-041	60	61	1	0.967	0.794	9	0.491	1.761
KZDD-041	61	62	1	0.479	0.241	2	0.094	0.72
KZDD-041	62	63	1	0.178	0.085	<1	0.027	0.263
KZDD-041	63	64	1	0.135	0.068	<1	0.033	0.203
KZDD-041	64	65	1	0.229	0.119	1	0.036	0.348
KZDD-041	65	66	1	1.96	0.842	7	0.124	2.802
KZDD-041	66	67	1	0.928	0.472	4	0.088	1.4
KZDD-041	67	67.5	0.5	1.3	0.633	5	0.115	1.933
KZDD-041	67.5	68.2	0.7	0.519	0.245	3	0.093	0.764
KZDD-041	68.2	69	0.8	0.17	0.091	1	0.041	0.261
KZDD-041	69	70	1	0.816	0.397	2	0.156	1.213
KZDD-041	70	71	1	0.575	0.27	1	0.127	0.845
KZDD-041	71	73	2	0.077	0.048	1	0.025	0.125
KZDD-041	73	75	2	0.032	0.022	<1	0.016	0.054
KZDD-041	75	77	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-041	77	79	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-041	79	81	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-041	81	83	2	0.012	<0.005	<1	<0.005	0.0145
KZDD-042	0	1	1	Not sampled				



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-042	1	2	1	0.359	0.502	5	0.054	0.861
KZDD-042	2	3	1	0.991	0.039	<1	0.005	1.03
KZDD-042	3	4	1	0.827	0.308	1	0.017	1.135
KZDD-042	4	5	1	1.48	0.629	5	0.022	2.109
KZDD-042	5	6	1	0.672	0.255	<1	0.008	0.927
KZDD-042	6	7	1	0.055	<0.005	<1	<0.005	0.0575
KZDD-042	7	8	1	0.246	0.114	<1	0.005	0.36
KZDD-042	8	9	1	0.308	0.202	2	0.025	0.51
KZDD-042	9	10	1	0.019	<0.005	<1	<0.005	0.0215
KZDD-042	10	11	1	0.022	<0.005	<1	<0.005	0.0245
KZDD-042	11	12	1	0.012	<0.005	<1	<0.005	0.0145
KZDD-042	12	13	1	0.115	0.062	<1	0.008	0.177
KZDD-042	13	13.7	0.7	0.895	0.368	2	0.125	1.263
KZDD-042	13.7	14.7	1	0.134	0.072	<1	0.01	0.206
KZDD-042	14.7	15.7	1	0.027	0.011	<1	0.005	0.038
KZDD-042	15.7	16.2	0.5	1.405	0.562	4	0.072	1.967
KZDD-042	16.2	17	0.8	0.543	0.288	2	0.046	0.831
KZDD-042	17	18	1	0.378	0.191	1	0.021	0.569
KZDD-042	18	18.7	0.7	2.42	1.345	11	1.215	3.765
KZDD-042	18.7	19.7	1	0.301	0.102	<1	0.167	0.403
KZDD-042	19.7	20.3	0.6	0.356	0.15	3	1.085	0.506
KZDD-042	20.3	21	0.7	0.028	0.014	<1	0.025	0.042
KZDD-042	21	22	1	0.014	<0.005	<1	0.148	0.0165
KZDD-042	22	23	1	0.023	0.014	<1	<0.005	0.037
KZDD-042	23	25	2	0.014	<0.005	<1	0.005	0.0165
KZDD-042	25	27	2	0.015	<0.005	<1	0.008	0.0175
KZDD-042	27	29	2	0.015	<0.005	<1	<0.005	0.0175
KZDD-042	29	30	1	0.055	0.392	2	0.023	0.447
KZDD-042	30	31	1	0.182	0.166	<1	0.054	0.348
KZDD-042	31	32	1	0.878	0.288	1	0.032	1.166
KZDD-042	32	34	2	0.043	0.038	<1	0.006	0.081
KZDD-042	34	35.5	1.5	0.031	0.017	<1	<0.005	0.048
KZDD-042	35.5	36	0.5	0.094	0.14	4	0.675	0.234
KZDD-042	36	37	1	0.015	<0.005	<1	0.124	0.0175
KZDD-042	37	38	1	0.021	<0.005	<1	0.309	0.0235
KZDD-042	38	39	1	0.02	0.005	1	0.194	0.025
KZDD-042	39	40	1	0.015	0.01	<1	0.02	0.025
KZDD-042	40	41	1	0.053	0.03	<1	0.005	0.083
KZDD-042	41	42	1	0.377	0.073	<1	0.099	0.45
KZDD-042	42	43	1	0.068	0.026	<1	0.025	0.094
KZDD-042	43	44	1	0.066	0.061	1	0.023	0.127
KZDD-042	44	44.5	0.5	0.074	0.05	<1	0.018	0.124
KZDD-042	44.5	46	1.5	0.027	0.012	<1	0.005	0.039
KZDD-042	46	48	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-042	48	50	2	0.005	<0.005	<1	0.005	0.0075
KZDD-042	50	52	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-042	52	54	2	0.018	0.005	<1	0.01	0.023
KZDD-042	54	56	2	0.013	<0.005	<1	0.007	0.0155
KZDD-042	56	58	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-042	58	59.5	1.5	0.023	<0.005	<1	<0.005	0.0255
KZDD-042	59.5	60	0.5	0.17	0.085	<1	0.018	0.255
KZDD-042	60	61	1	0.153	0.11	<1	<0.005	0.263
KZDD-042	61	62	1	0.521	0.251	2	0.194	0.772
KZDD-042	62	63	1	0.18	0.094	1	0.232	0.274
KZDD-042	63	65	2	0.015	<0.005	1	0.006	0.0175
KZDD-042	65	67	2	0.022	0.012	<1	<0.005	0.034



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-042	67	69	2	0.018	<0.005	<1	0.012	0.0205
KZDD-042	69	70.8	1.8	0.18	0.105	<1	0.021	0.285
KZDD-042	70.8	71.7	0.9	0.815	0.38	4	0.168	1.195
KZDD-042	71.7	72.6	0.9	4.02	1.65	19	0.312	5.67
KZDD-042	72.6	73.2	0.6	6.06	2.84	45	0.514	8.9
KZDD-042	73.2	74	0.8	1.835	0.787	10	0.47	2.622
KZDD-042	74	75	1	1.72	1.115	20	0.281	2.835
KZDD-042	75	76	1	3.77	1.835	24	1.405	5.605
KZDD-042	76	77	1	1.15	1.055	10	0.501	2.205
KZDD-042	77	78	1	0.984	0.499	4	0.147	1.483
KZDD-042	78	79	1	1.805	0.406	3	0.074	2.211
KZDD-042	79	80	1	1.7	1.06	9	0.037	2.76
KZDD-042	80	81	1	1.005	0.505	1	0.028	1.51
KZDD-042	81	83	2	0.109	0.069	<1	0.015	0.178
KZDD-042	83	85	2	0.171	0.08	2	0.049	0.251
KZDD-042	85	86	1	0.073	0.046	<1	0.008	0.119
KZDD-042	86	87	1	0.275	0.128	<1	0.023	0.403
KZDD-042	87	88	1	0.6	0.6	6	0.028	1.2
KZDD-042	88	89	1	0.324	0.118	<1	0.032	0.442
KZDD-042	89	91	2	0.064	0.03	<1	0.009	0.094
KZDD-042	91	92	1	0.201	0.149	2	0.018	0.35
KZDD-042	92	93	1	0.33	0.156	6	0.063	0.486
KZDD-042	93	94	1	0.365	0.137	1	0.055	0.502
KZDD-042	94	95	1	0.845	0.388	1	0.109	1.233
KZDD-042	95	96	1	1.08	0.843	5	0.084	1.923
KZDD-042	96	97	1	0.467	0.248	4	0.089	0.715
KZDD-042	97	98	1	1.275	0.955	11	0.113	2.23
KZDD-042	98	99	1	2.74	1.24	11	0.123	3.98
KZDD-042	99	100	1	0.222	0.125	2	0.019	0.347
KZDD-042	100	101	1	3.36	0.985	14	0.14	4.345
KZDD-042	101	102	1	0.836	0.35	5	0.113	1.186
KZDD-042	102	104	2	0.535	0.272	3	0.05	0.807
KZDD-042	104	106	2	0.026	0.012	<1	0.014	0.038
KZDD-042	106	107	1	0.053	0.028	<1	0.033	0.081
KZDD-042	107	108	1	0.059	0.016	<1	0.015	0.075
KZDD-042	108	110	2	0.095	0.036	1	0.046	0.131
KZDD-042	110	111	1	0.286	0.13	1	0.149	0.416
KZDD-042	111	112	1	0.089	0.383	2	0.093	0.472
KZDD-042	112	113	1	0.221	0.122	<1	0.049	0.343
KZDD-042	113	114	1	0.146	0.048	<1	0.073	0.194
KZDD-042	114	115	1	0.686	0.15	1	0.058	0.836
KZDD-042	115	116	1	1.78	0.67	7	0.226	2.45
KZDD-042	116	117	1	1.355	0.36	3	0.186	1.715
KZDD-042	117	118	1	0.244	0.181	<1	0.058	0.425
KZDD-042	118	120	2	0.081	0.031	<1	0.009	0.112
KZDD-042	120	122	2	0.014	0.006	<1	0.005	0.02
KZDD-042	122	124	2	0.008	0.007	<1	0.009	0.015
KZDD-042	124	125.5	1.5	0.058	0.017	<1	0.011	0.075
KZDD-042	125.5	126	0.5	0.879	0.297	1	0.065	1.176
KZDD-042	126	128	2	0.01	0.005	<1	0.01	0.015
KZDD-042	128	129	1	0.33	0.194	<1	0.103	0.524
KZDD-042	129	129.5	0.5	2.38	0.924	14	0.112	3.304
KZDD-042	129.5	131	1.5	0.05	0.026	<1	0.035	0.076
KZDD-042	131	133	2	0.01	<0.005	<1	0.015	0.0125
KZDD-042	133	134.5	1.5	0.01	0.007	<1	0.018	0.017
KZDD-042	134.5	135	0.5	0.388	0.178	4	0.202	0.566



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-042	135	137	2	0.021	0.011	<1	0.011	0.032
KZDD-042	137	139	2	0.007	<0.005	<1	0.007	0.0095
KZDD-042	139	140.4	1.4	0.016	0.019	<1	0.034	0.035
KZDD-042	140.4	141	0.6	0.366	0.137	<1	0.086	0.503
KZDD-042	141	143	2	0.013	<0.005	<1	<0.005	0.0155
KZDD-042	143	145	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-042	145	147	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-042	147	149	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-042	149	151	2	<0.005	<0.005	<1	<0.005	<0.005
KZDD-043	0	0.9	0.9	Not sampled				
KZDD-043	0.9	2	1.1	0.05	0.077	<1	0.009	0.127
KZDD-043	2	3	1	0.022	0.016	<1	<0.005	0.038
KZDD-043	3	4	1	0.01	0.009	<1	<0.005	0.019
KZDD-043	4	5	1	0.027	0.012	<1	<0.005	0.039
KZDD-043	5	6	1	0.051	0.01	<1	<0.005	0.061
KZDD-043	6	7	1	0.01	0.011	<1	<0.005	0.021
KZDD-043	7	8	1	0.008	0.005	<1	<0.005	0.013
KZDD-043	8	9	1	0.008	<0.005	<1	<0.005	0.0105
KZDD-043	9	10	1	0.005	<0.005	<1	<0.005	0.0075
KZDD-043	10	11	1	0.009	0.006	<1	<0.005	0.015
KZDD-043	11	12	1	0.006	<0.005	<1	<0.005	0.0085
KZDD-043	12	13	1	0.013	<0.005	<1	<0.005	0.0155
KZDD-043	13	14	1	0.016	0.01	<1	0.005	0.026
KZDD-043	14	14.5	0.5	0.026	0.035	1	<0.005	0.061
KZDD-043	14.5	15.1	0.6	0.018	0.028	1	<0.005	0.046
KZDD-043	15.1	16	0.9	0.499	0.324	6	0.046	0.823
KZDD-043	16	17.5	1.5	1.63	1.095	14	0.095	2.725
KZDD-043	17.5	19.5	2	0.4	0.278	2	0.053	0.678
KZDD-043	19.5	21.5	2	0.749	0.99	10	0.063	1.739
KZDD-043	21.5	22	0.5	0.215	0.125	1	0.038	0.34
KZDD-043	22	23	1	0.084	0.068	<1	0.013	0.152
KZDD-043	23	24	1	0.073	0.032	1	0.03	0.105
KZDD-043	24	25	1	0.326	0.704	16	0.155	1.03
KZDD-043	25	26	1	0.914	1.245	17	0.459	2.159
KZDD-043	26	27	1	0.397	0.329	3	0.07	0.726
KZDD-043	27	28	1	0.015	0.016	<1	0.029	0.031
KZDD-043	28	29	1	0.344	0.257	2	0.063	0.601
KZDD-043	29	30	1	0.362	0.218	3	0.086	0.58
KZDD-043	30	31.6	1.6	Not sampled				
KZDD-043	31.6	32.8	1.2	0.331	0.366	12	0.228	0.697
KZDD-043	32.8	36	3.2	0.391	0.44	12	0.254	0.831
KZDD-043	36	38.6	2.6	Not sampled				
KZDD-043	38.6	39.5	0.9	1.66	1.315	12	0.074	2.975
KZDD-043	39.5	40	0.5	1.655	1.235	12	0.081	2.89
KZDD-043	40	41	1	1.185	0.732	9	0.069	1.917
KZDD-043	41	42	1	1.42	1.14	12	0.096	2.56
KZDD-043	42	42.6	0.6	1.12	0.636	7	0.116	1.756
KZDD-043	42.6	47.9	5.3	Not sampled				
KZDD-043	47.9	49.5	1.6	0.06	0.059	<1	0.027	0.119
KZDD-043	49.5	51.5	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-043	51.5	52	0.5	0.006	<0.005	<1	<0.005	0.0085
KZDD-043	52	54	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-043	54	55.8	1.8	0.01	0.008	<1	<0.005	0.018
KZDD-043	55.8	56.6	0.8	0.214	0.071	<1	0.011	0.285
KZDD-043	56.6	57.5	0.9	0.01	0.005	1	<0.005	0.015
KZDD-043	57.5	58.3	0.8	0.044	0.033	<1	0.022	0.077



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-043	58.3	58.8	0.5	0.009	0.006	<1	<0.005	0.015
KZDD-043	58.8	60.5	1.7	0.009	<0.005	<1	<0.005	0.0115
KZDD-043	60.5	62.5	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-043	62.5	64.5	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-043	64.5	66.5	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-043	66.5	67.2	0.7	0.065	0.052	1	0.022	0.117
KZDD-043	67.2	68	0.8	0.101	0.069	<1	0.016	0.17
KZDD-043	68	69	1	1.685	0.686	6	0.139	2.371
KZDD-043	69	69.7	0.7	0.111	0.07	<1	0.028	0.181
KZDD-043	69.7	70.2	0.5	0.145	0.072	<1	0.114	0.217
KZDD-043	70.2	71	0.8	0.011	0.013	<1	0.011	0.024
KZDD-043	71	73	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-043	73	75	2	0.006	<0.005	<1	0.008	0.0085
KZDD-043	75	77	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-043	77	79	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-043	79	81	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-043	81	98	17	Not sampled				
KZDD-043	98	100	2	0.015	<0.005	1	<0.005	0.0175
KZDD-043	100	102	2	0.014	<0.005	<1	<0.005	0.0165
KZDD-043	102	104	2	0.016	<0.005	<1	<0.005	0.0185
KZDD-043	104	106	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-043	106	108	2	0.014	<0.005	<1	<0.005	0.0165
KZDD-043	108	109	1	0.062	0.037	1	0.036	0.099
KZDD-043	109	110	1	2.06	0.523	5	0.246	2.583
KZDD-043	110	111	1	0.099	0.06	1	0.091	0.159
KZDD-043	111	112	1	0.009	<0.005	<1	<0.005	0.0115
KZDD-043	112	113	1	0.223	0.092	1	0.061	0.315
KZDD-043	113	114	1	0.316	0.199	1	0.098	0.515
KZDD-043	114	115	1	0.271	0.128	3	0.099	0.399
KZDD-043	115	115.5	0.5	1.55	0.551	7	0.301	2.101
KZDD-043	115.5	116.2	0.7	0.739	0.411	4	0.203	1.15
KZDD-043	116.2	116.7	0.5	0.068	0.021	<1	0.031	0.089
KZDD-043	116.7	117.3	0.6	0.659	0.271	1	0.166	0.93
KZDD-043	117.3	118.3	1	0.023	0.005	1	0.015	0.028
KZDD-043	118.3	119.2	0.9	0.415	0.14	<1	0.073	0.555
KZDD-043	119.2	119.8	0.6	3.67	0.358	7	0.502	4.028
KZDD-043	119.8	120.3	0.5	0.47	0.325	5	0.413	0.795
KZDD-043	120.3	121	0.7	0.397	0.271	5	0.35	0.668
KZDD-043	121	122	1	0.351	0.182	2	0.207	0.533
KZDD-043	122	123	1	0.421	0.2	3	0.223	0.621
KZDD-043	123	124	1	2.16	0.453	8	0.371	2.613
KZDD-043	124	125	1	1.095	0.669	8	0.409	1.764
KZDD-043	125	126	1	2.17	0.281	4	0.306	2.451
KZDD-043	126	128	2	0.016	0.006	<1	0.012	0.022
KZDD-043	128	130	2	0.013	<0.005	<1	0.012	0.0155
KZDD-043	130	132	2	0.011	<0.005	<1	0.007	0.0135
KZDD-043	132	134	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-043	134	136	2	0.009	<0.005	<1	0.008	0.0115
KZDD-043	136	138	2	0.01	<0.005	<1	0.006	0.0125
KZDD-043	138	148	10	Not sampled				
KZDD-043	148	150	2	0.011	0.007	<1	0.017	0.018
KZDD-043	150	152	2	0.018	<0.005	<1	0.008	0.0205
KZDD-043	152	154	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-043	154	156	2	0.012	<0.005	<1	<0.005	0.0145
KZDD-043	156	158	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-043	158	159	1	0.021	0.014	<1	0.053	0.035



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-043	159	160	1	0.019	0.005	<1	0.01	0.024
KZDD-043	160	161	1	0.035	0.015	<1	0.018	0.05
KZDD-043	161	163	2	0.024	0.008	<1	<0.005	0.032
KZDD-043	163	165	2	0.024	0.012	<1	0.008	0.036
KZDD-043	165	167	2	0.023	0.007	<1	<0.005	0.03
KZDD-043	167	169	2	0.016	0.008	1	0.015	0.024
KZDD-043	169	171	2	0.013	<0.005	<1	<0.005	0.0155
KZDD-043	171	173	2	0.015	0.006	<1	0.005	0.021
KZDD-043	173	175	2	0.014	<0.005	1	<0.005	0.0165
KZDD-043	175	177	2	0.024	0.007	<1	<0.005	0.031
KZDD-043	177	177.5	0.5	0.036	0.025	<1	0.007	0.061
KZDD-043	177.5	178	0.5	0.06	0.023	<1	0.04	0.083
KZDD-043	178	179	1	0.047	0.027	<1	0.04	0.074
KZDD-043	179	180	1	0.046	0.077	1	0.125	0.123
KZDD-043	180	181	1	0.035	0.018	<1	0.016	0.053
KZDD-043	181	183	2	0.015	<0.005	1	<0.005	0.0175
KZDD-043	183	185	2	0.019	0.007	<1	0.009	0.026
KZDD-043	185	187	2	0.072	0.052	1	0.024	0.124
KZDD-043	187	189	2	0.078	0.034	<1	0.019	0.112
KZDD-043	189	191	2	0.065	0.026	<1	0.022	0.091
KZDD-043	191	200.5	9.5	Not sampled				
KZDD-043	200.5	206.1	5.6	0.005	<0.005	<1	<0.005	0.0075
KZDD-043	206.1	208	1.9	0.012	<0.005	<1	0.008	0.0145
KZDD-043	208	210	2	0.065	0.034	<1	0.051	0.099
KZDD-043	210	212	2	0.075	0.038	<1	0.016	0.113
KZDD-043	212	214	2	0.032	0.013	<1	0.016	0.045
KZDD-043	214	215	1	0.03	0.015	<1	0.027	0.045
KZDD-043	215	216	1	0.026	0.016	<1	0.024	0.042
KZDD-043	216	217	1	0.012	<0.005	<1	0.007	0.0145
KZDD-043	217	218	1	0.017	0.005	<1	0.019	0.022
KZDD-043	218	219	1	0.014	0.006	<1	0.045	0.02
KZDD-043	219	220	1	0.041	0.023	1	0.012	0.064
KZDD-043	220	221	1	0.018	0.006	<1	0.009	0.024
KZDD-043	221	222	1	0.015	<0.005	<1	0.014	0.0175
KZDD-043	222	223	1	0.009	0.006	<1	0.04	0.015
KZDD-043	223	225	2	0.013	0.005	<1	0.031	0.018
KZDD-043	225	226	1	0.014	0.01	<1	0.055	0.024
KZDD-043	226	227	1	0.264	0.093	<1	0.155	0.357
KZDD-043	227	228	1	0.024	0.128	<1	0.02	0.152
KZDD-043	228	230	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-043	230	232	2	0.008	<0.005	<1	0.005	0.0105
KZDD-043	232	234	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-043	234	236	2	0.012	0.022	<1	<0.005	0.034
KZDD-043	236	241	5	Not sampled				
KZDD-043	241	243	2	0.044	0.018	<1	0.012	0.062
KZDD-043	243	245	2	0.047	0.027	<1	0.033	0.074
KZDD-043	245	247	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-043	247	249	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-043	249	251	2	0.111	0.048	<1	0.027	0.159
KZDD-043	251	251.5	0.5	0.094	0.07	<1	0.05	0.164
KZDD-043	251.5	252	0.5	0.066	0.04	<1	0.049	0.106
KZDD-043	252	254	2	0.059	0.021	<1	0.021	0.08
KZDD-043	254	256	2	0.273	0.14	1	0.015	0.413
KZDD-043	256	258	2	0.03	0.01	<1	<0.005	0.04
KZDD-043	258	260	2	0.016	<0.005	<1	<0.005	0.0185
KZDD-043	260	262	2	0.014	<0.005	<1	0.007	0.0165



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-043	262	264	2	0.011	<0.005	<1	0.012	0.0135
KZDD-043	264	266	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-043	266	268	2	0.008	<0.005	1	0.006	0.0105
KZDD-043	268	270	2	0.018	0.007	<1	0.008	0.025
KZDD-043	270	270.9	0.9	0.099	0.063	<1	0.029	0.162
KZDD-043	270.9	271.9	1	0.177	0.071	<1	0.037	0.248
KZDD-043	271.9	273	1.1	0.034	0.014	1	0.009	0.048
KZDD-043	273	275	2	0.029	0.007	2	0.008	0.036
KZDD-043	275	276.7	1.7	0.053	0.02	2	0.016	0.073
KZDD-043	276.7	277.3	0.6	0.581	0.124	2	0.045	0.705
KZDD-043	277.3	278	0.7	0.084	0.174	1	0.032	0.258
KZDD-043	278	280	2	0.028	0.026	1	0.013	0.054
KZDD-043	280	282	2	0.177	0.234	3	0.042	0.411
KZDD-043	282	284	2	0.034	0.01	1	0.009	0.044
KZDD-043	284	286	2	0.02	0.033	<1	0.008	0.053
KZDD-043	286	288	2	0.154	0.139	1	0.028	0.293
KZDD-045	0	2	2	Not sampled				
KZDD-045	2	3	1	0.244	0.035	3	0.024	0.279
KZDD-045	3	4	1	0.412	0.028	1	0.021	0.44
KZDD-045	4	5	1	0.285	0.129	3	0.032	0.414
KZDD-045	5	6	1	0.477	0.445	8	0.038	0.922
KZDD-045	6	7.1	1.1	0.177	0.111	2	0.027	0.288
KZDD-045	7.1	8	0.9	0.812	0.44	5	0.099	1.252
KZDD-045	8	9	1	2.07	1	13	0.281	3.07
KZDD-045	9	10	1	0.808	0.105	1	0.034	0.913
KZDD-045	10	11	1	0.287	0.007	<1	0.006	0.294
KZDD-045	11	13	2	0.017	<0.005	<1	0.006	0.0195
KZDD-045	13	15	2	0.009	<0.005	1	0.005	0.0115
KZDD-045	15	17	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-045	17	19	2	0.007	<0.005	1	0.023	0.0095
KZDD-045	19	21	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-045	21	104	83	Not sampled				
KZDD-045	104	106	2	0.008	<0.005	1	<0.005	0.0105
KZDD-045	106	108	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-045	108	110	2	0.01	<0.005	1	0.006	0.0125
KZDD-045	110	112	2	0.014	<0.005	1	0.019	0.0165
KZDD-045	112	114	2	0.019	0.032	<1	0.024	0.051
KZDD-045	114	115	1	0.076	0.044	2	0.034	0.12
KZDD-045	115	117	2	2.72	0.603	3	0.032	3.323
KZDD-045	117	119	2	0.054	0.024	1	0.005	0.078
KZDD-045	119	121	2	0.026	0.013	<1	0.006	0.039
KZDD-045	121	123	2	0.023	0.017	1	0.022	0.04
KZDD-045	123	125	2	0.074	0.055	1	0.012	0.129
KZDD-045	125	127	2	0.043	0.024	<1	0.026	0.067
KZDD-045	127	128	1	0.185	0.1	1	0.038	0.285
KZDD-045	128	128.8	0.8	0.185	0.106	<1	0.134	0.291
KZDD-045	128.8	129.3	0.5	1.295	1.4	10	0.122	2.695
KZDD-045	129.3	130	0.7	0.279	0.112	2	0.116	0.391
KZDD-045	130	132	2	0.019	0.018	1	0.023	0.037
KZDD-045	132	134	2	0.017	0.012	<1	0.009	0.029
KZDD-045	134	136	2	0.013	<0.005	<1	0.005	0.0155
KZDD-045	136	138	2	0.028	0.027	<1	0.008	0.055
KZDD-045	138	140	2	0.025	0.03	1	<0.005	0.055
KZDD-045	140	142	2	0.033	0.025	<1	0.006	0.058
KZDD-045	142	144	2	0.035	0.014	<1	0.014	0.049
KZDD-045	144	145	1	0.023	0.01	2	0.025	0.033



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-045	145	146	1	0.462	0.232	4	0.195	0.694
KZDD-045	146	147	1	0.406	0.245	2	0.107	0.651
KZDD-045	147	149	2	0.092	0.048	1	0.019	0.14
KZDD-045	149	151	2	0.024	0.011	2	0.009	0.035
KZDD-045	151	153	2	0.024	0.01	2	0.013	0.034
KZDD-045	153	155	2	0.009	<0.005	2	<0.005	0.0115
KZDD-045	155	157	2	0.007	<0.005	<1	0.005	0.0095
KZDD-045	157	161	4	Not sampled				
KZDD-045	161	162.5	1.5	0.011	<0.005	1	0.005	0.0135
KZDD-045	162.5	163.3	0.8	0.457	0.265	3	0.058	0.722
KZDD-045	163.3	165	1.7	0.018	<0.005	1	0.032	0.0205
KZDD-045	165	181	16	Not sampled				
KZDD-045	181	183	2	0.009	<0.005	2	0.006	0.0115
KZDD-045	183	185	2	0.023	<0.005	<1	0.008	0.0255
KZDD-045	185	187	2	0.013	<0.005	1	0.013	0.0155
KZDD-045	187	189	2	0.02	0.013	1	0.01	0.033
KZDD-045	189	191	2	0.02	0.01	1	0.014	0.03
KZDD-045	191	192.5	1.5	0.035	0.018	<1	0.013	0.053
KZDD-045	192.5	193	0.5	0.011	<0.005	<1	<0.005	0.0135
KZDD-045	193	194	1	0.17	0.074	<1	0.016	0.244
KZDD-045	194	195	1	0.093	0.04	2	0.006	0.133
KZDD-045	195	197	2	0.021	<0.005	3	0.008	0.0235
KZDD-045	197	199	2	0.021	0.008	<1	0.201	0.029
KZDD-045	199	200	1	0.307	0.137	2	0.066	0.444
KZDD-045	200	201	1	0.221	0.099	1	0.068	0.32
KZDD-045	201	202	1	0.29	0.115	2	0.096	0.405
KZDD-045	202	203	1	0.302	0.103	5	0.225	0.405
KZDD-045	203	204	1	0.031	0.013	<1	0.221	0.044
KZDD-045	204	205	1	0.032	0.01	<1	0.036	0.042
KZDD-045	205	206	1	0.08	0.032	1	0.026	0.112
KZDD-045	206	207	1	0.13	0.746	8	0.082	0.876
KZDD-045	207	208	1	0.213	0.066	2	0.064	0.279
KZDD-045	208	209	1	0.045	0.029	1	0.025	0.074
KZDD-045	209	210	1	0.193	0.131	2	0.055	0.324
KZDD-045	210	211	1	0.16	0.072	2	0.076	0.232
KZDD-045	211	212	1	0.154	0.091	1	0.065	0.245
KZDD-045	212	214	2	0.045	0.038	1	0.033	0.083
KZDD-045	214	216	2	0.073	0.037	2	0.02	0.11
KZDD-045	216	217	1	0.149	0.098	2	0.078	0.247
KZDD-045	217	218	1	0.085	0.033	2	0.028	0.118
KZDD-045	218	219	1	0.546	0.218	3	0.101	0.764
KZDD-045	219	220	1	0.458	0.167	2	0.058	0.625
KZDD-045	220	221	1	0.296	0.142	3	0.123	0.438
KZDD-045	221	222	1	0.011	0.005	1	0.051	0.016
KZDD-045	222	223	1	0.029	0.018	1	0.05	0.047
KZDD-045	223	224	1	0.01	<0.005	<1	0.018	0.0125
KZDD-045	224	226	2	0.049	0.016	1	0.013	0.065
KZDD-045	226	226.7	0.7	0.376	0.185	2	0.052	0.561
KZDD-045	226.7	227.5	0.8	1.16	0.636	6	0.137	1.796
KZDD-045	227.5	228	0.5	0.723	0.526	5	0.108	1.249
KZDD-045	228	229	1	0.32	0.174	2	0.042	0.494
KZDD-045	229	230	1	2.18	0.917	12	0.307	3.097
KZDD-045	230	231	1	0.498	0.087	2	0.028	0.585
KZDD-045	231	233	2	0.009	<0.005	1	0.009	0.0115
KZDD-045	233	235	2	0.008	<0.005	<1	0.006	0.0105
KZDD-045	235	237	2	0.007	<0.005	1	<0.005	0.0095



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-045	237	239	2	0.009	<0.005	2	0.008	0.0115
KZDD-045	239	241	2	0.014	<0.005	1	0.008	0.0165
KZDD-045	241	296.6	55.6	Not sampled				
KZDD-046	0	81	81	Not sampled				
KZDD-046	81	83	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-046	83	85	2	0.009	<0.005	<1	0.008	0.0115
KZDD-046	85	87	2	0.006	<0.005	<1	0.006	0.0085
KZDD-046	87	89	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-046	89	91	2	0.014	<0.005	<1	0.01	0.0165
KZDD-046	91	91.6	0.6	0.309	0.111	1	0.053	0.42
KZDD-046	91.6	92.2	0.6	0.056	0.024	1	0.019	0.08
KZDD-046	92.2	93	0.8	0.051	0.021	<1	0.018	0.072
KZDD-046	93	94	1	0.252	0.133	2	0.062	0.385
KZDD-046	94	95	1	0.038	0.019	1	0.081	0.057
KZDD-046	95	96	1	0.042	0.017	<1	0.016	0.059
KZDD-046	96	97	1	0.016	0.016	<1	0.049	0.032
KZDD-046	97	98	1	0.017	0.009	1	0.009	0.026
KZDD-046	98	99	1	0.027	0.014	<1	0.026	0.041
KZDD-046	99	100	1	0.074	0.049	1	0.102	0.123
KZDD-046	100	101	1	0.736	0.329	6	0.148	1.065
KZDD-046	101	102	1	0.313	0.198	4	0.114	0.511
KZDD-046	102	103	1	0.409	0.147	6	0.065	0.556
KZDD-046	103	104	1	0.088	0.052	3	0.053	0.14
KZDD-046	104	105	1	0.054	0.031	1	0.015	0.085
KZDD-046	105	107	2	0.014	0.005	<1	0.006	0.019
KZDD-046	107	108	1	0.059	0.012	<1	0.012	0.071
KZDD-046	108	109	1	0.025	0.022	1	0.009	0.047
KZDD-046	109	110	1	0.427	0.197	5	0.091	0.624
KZDD-046	110	111	1	0.123	0.069	2	0.054	0.192
KZDD-046	111	113	2	0.036	0.027	2	0.085	0.063
KZDD-046	113	115	2	0.011	<0.005	1	<0.005	0.0135
KZDD-046	115	116	1	0.043	0.021	1	0.052	0.064
KZDD-046	116	117	1	0.093	0.044	2	0.105	0.137
KZDD-046	117	118	1	0.028	0.013	2	0.112	0.041
KZDD-046	118	119	1	0.227	0.057	4	0.425	0.284
KZDD-046	119	120	1	0.025	0.028	2	0.072	0.053
KZDD-046	120	121	1	0.019	0.009	1	0.026	0.028
KZDD-046	121	123	2	0.013	<0.005	<1	0.005	0.0155
KZDD-046	123	125	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-046	125	127	2	0.014	<0.005	<1	0.008	0.0165
KZDD-046	127	129	2	0.014	<0.005	<1	0.005	0.0165
KZDD-046	129	131	2	0.061	0.023	1	0.032	0.084
KZDD-046	131	132.5	1.5	0.033	0.018	<1	0.013	0.051
KZDD-046	132.5	133.5	1	0.336	0.15	4	0.056	0.486
KZDD-046	133.5	134.5	1	0.408	0.235	6	0.09	0.643
KZDD-046	134.5	135	0.5	0.035	0.025	2	0.03	0.06
KZDD-046	135	137	2	0.018	0.009	1	0.005	0.027
KZDD-046	137	139	2	0.033	0.017	1	0.016	0.05
KZDD-046	139	141	2	0.1	0.05	2	0.042	0.15
KZDD-046	141	143	2	0.014	<0.005	1	0.005	0.0165
KZDD-046	143	145	2	0.016	<0.005	<1	<0.005	0.0185
KZDD-046	145	147	2	0.016	<0.005	<1	<0.005	0.0185
KZDD-046	147	149	2	0.017	<0.005	<1	<0.005	0.0195
KZDD-046	149	151	2	0.091	0.042	2	0.038	0.133
KZDD-046	151	152	1	0.095	0.063	1	0.023	0.158
KZDD-046	152	153	1	0.189	0.11	3	0.049	0.299



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-046	153	155	2	0.013	<0.005	<1	0.005	0.0155
KZDD-046	155	156.5	1.5	0.043	0.024	<1	0.018	0.067
KZDD-046	156.5	157.5	1	1.035	0.436	11	0.14	1.471
KZDD-046	157.5	158	0.5	1.33	0.336	15	0.117	1.666
KZDD-046	158	159	1	0.375	0.198	5	0.07	0.573
KZDD-046	159	160	1	0.335	0.153	3	0.058	0.488
KZDD-046	160	161	1	0.706	0.177	7	0.094	0.883
KZDD-046	161	162	1	0.202	0.126	3	0.04	0.328
KZDD-046	162	163	1	0.419	0.157	5	0.131	0.576
KZDD-046	163	165	2	0.019	0.014	<1	0.015	0.033
KZDD-046	165	166.5	1.5	0.01	<0.005	<1	0.007	0.0125
KZDD-046	166.5	167	0.5	1.87	2.89	70	0.194	4.76
KZDD-046	167	169	2	0.109	0.093	4	0.024	0.202
KZDD-046	169	170	1	0.179	0.165	4	0.04	0.344
KZDD-046	170	171	1	0.615	0.206	8	0.098	0.821
KZDD-046	171	172	1	0.284	0.07	4	0.057	0.354
KZDD-046	172	173	1	0.241	0.148	4	0.066	0.389
KZDD-046	173	174	1	0.22	0.092	3	0.05	0.312
KZDD-046	174	175	1	0.292	0.137	4	0.053	0.429
KZDD-046	175	176	1	0.147	0.046	3	0.056	0.193
KZDD-046	176	177	1	0.806	0.316	8	0.074	1.122
KZDD-046	177	178	1	0.248	0.127	5	0.088	0.375
KZDD-046	178	179	1	0.895	0.35	9	0.088	1.245
KZDD-046	179	180	1	0.299	0.095	3	0.065	0.394
KZDD-046	180	181	1	0.051	0.035	1	0.042	0.086
KZDD-046	181	182	1	0.014	0.009	1	0.011	0.023
KZDD-046	182	183	1	0.098	0.06	3	0.03	0.158
KZDD-046	183	184	1	0.828	0.385	9	0.121	1.213
KZDD-046	184	185	1	0.588	0.25	6	0.112	0.838
KZDD-046	185	186	1	0.626	0.387	5	0.11	1.013
KZDD-046	186	187	1	0.068	0.043	1	0.028	0.111
KZDD-046	187	188	1	0.022	0.012	<1	0.01	0.034
KZDD-046	188	189	1	0.456	0.221	3	0.073	0.677
KZDD-046	189	190	1	1.66	0.451	6	0.117	2.111
KZDD-046	190	191	1	0.091	0.095	1	0.035	0.186
KZDD-046	191	192	1	0.103	0.068	1	0.042	0.171
KZDD-046	192	193	1	0.104	0.069	1	0.071	0.173
KZDD-046	193	194	1	0.108	0.053	2	0.038	0.161
KZDD-046	194	195	1	0.168	0.067	2	0.027	0.235
KZDD-046	195	196	1	0.702	0.127	4	0.074	0.829
KZDD-046	196	197	1	0.324	0.132	6	0.26	0.456
KZDD-046	197	198	1	0.526	0.284	6	0.216	0.81
KZDD-046	198	199	1	0.281	0.138	3	0.114	0.419
KZDD-046	199	200	1	0.239	0.103	11	0.641	0.342
KZDD-046	200	201	1	0.017	0.019	1	0.04	0.036
KZDD-046	201	203	2	0.011	<0.005	<1	0.02	0.0135
KZDD-046	203	205	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-046	205	207	2	<0.005	<0.005	<1	0.026	0.0065
KZDD-046	207	209	2	0.011	<0.005	<1	0.008	0.0135
KZDD-046	209	211	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-046	211	213	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-046	213	215	2	0.007	<0.005	<1	0.007	0.0095
KZDD-046	215	217	2	0.144	0.081	2	0.055	0.225
KZDD-046	217	218	1	0.271	0.81	11	0.41	1.081
KZDD-046	218	219	1	0.372	0.959	13	0.162	1.331
KZDD-046	219	220	1	0.005	<0.005	<1	<0.005	0.0075



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-046	220	221	1	<0.005	<0.005	<1	<0.005	0.0065
KZDD-046	221	222	1	0.009	<0.005	<1	<0.005	0.0115
KZDD-046	222	224	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-046	224	226	2	0.009	<0.005	<1	0.009	0.0115
KZDD-046	226	228	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-046	228	230	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-046	230	232	2	0.008	<0.005	<1	0.01	0.0105
KZDD-047	0	1.5	1.5	0.133	0.05	1	0.007	0.183
KZDD-047	1.5	3	1.5	0.135	0.029	<1	0.005	0.164
KZDD-047	3	4.4	1.4	0.129	0.017	<1	0.008	0.146
KZDD-047	4.4	7.4	3	0.126	0.095	2	0.018	0.221
KZDD-047	7.4	8.9	1.5	0.296	0.23	3	0.029	0.526
KZDD-047	8.9	10.4	1.5	0.151	0.082	1	0.034	0.233
KZDD-047	10.4	11.9	1.5	0.454	0.219	2	0.212	0.673
KZDD-047	11.9	13.4	1.5	0.231	0.115	3	0.172	0.346
KZDD-047	13.4	14.3	0.9	0.16	0.116	<1	0.051	0.276
KZDD-047	14.3	14.9	0.6	0.596	0.465	3	0.105	1.061
KZDD-047	14.9	16.4	1.5	0.163	0.122	<1	0.039	0.285
KZDD-047	16.4	17.9	1.5	0.42	0.176	2	0.097	0.596
KZDD-047	17.9	18.7	0.8	9.02	4.64	50	0.215	13.66
KZDD-047	18.7	19.8	1.1	1.06	0.453	4	0.212	1.513
KZDD-047	19.8	20.8	1	0.03	0.03	<1	0.038	0.06
KZDD-047	20.8	21.5	0.7	0.011	0.006	<1	0.029	0.017
KZDD-047	21.5	23.5	2	0.011	<0.005	<1	0.016	0.0135
KZDD-047	23.5	24	0.5	0.029	0.169	<1	0.018	0.198
KZDD-047	24	25	1	0.014	0.006	<1	0.016	0.02
KZDD-047	25	27	2	0.015	0.012	<1	0.011	0.027
KZDD-047	27	28	1	0.04	0.013	<1	0.012	0.053
KZDD-047	28	29	1	0.207	0.092	<1	0.009	0.299
KZDD-047	29	30	1	0.055	0.023	<1	0.006	0.078
KZDD-047	30	31	1	0.027	0.015	<1	0.013	0.042
KZDD-047	31	32	1	0.015	0.011	<1	0.013	0.026
KZDD-047	32	33	1	0.013	0.006	<1	0.025	0.019
KZDD-047	33	34	1	0.044	0.036	<1	0.024	0.08
KZDD-047	34	36	2	0.026	0.012	<1	0.016	0.038
KZDD-047	36	38	2	0.051	0.028	1	0.019	0.079
KZDD-047	38	39	1	0.017	0.007	1	0.078	0.024
KZDD-047	39	40	1	0.09	0.055	2	0.201	0.145
KZDD-047	40	41	1	0.018	0.007	<1	0.062	0.025
KZDD-047	41	43	2	0.038	0.009	1	0.029	0.047
KZDD-047	43	45	2	0.103	0.035	<1	0.006	0.138
KZDD-047	45	46	1	0.036	0.021	<1	0.01	0.057
KZDD-047	46	47	1	0.066	0.026	1	0.082	0.092
KZDD-047	47	49	2	0.126	0.059	<1	0.013	0.185
KZDD-047	49	51	2	0.017	0.006	<1	<0.005	0.023
KZDD-047	51	53	2	0.026	0.025	<1	0.013	0.051
KZDD-047	53	55	2	0.095	0.018	2	0.164	0.113
KZDD-047	55	57	2	0.028	<0.005	<1	<0.005	0.0305
KZDD-047	57	59	2	0.016	<0.005	1	<0.005	0.0185
KZDD-047	59	140	81	Not sampled				
KZDD-047	140	142	2	0.018	<0.005	1	<0.005	0.0205
KZDD-047	142	144	2	0.013	<0.005	<1	0.007	0.0155
KZDD-047	144	146	2	0.012	<0.005	<1	0.007	0.0145
KZDD-047	146	148	2	0.019	<0.005	<1	0.012	0.0215
KZDD-047	148	150	2	0.056	0.011	<1	0.011	0.067
KZDD-047	150	151	1	0.098	0.031	1	0.22	0.129



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-047	151	152	1	0.025	0.013	<1	0.169	0.038
KZDD-047	152	153	1	0.015	0.013	2	0.097	0.028
KZDD-047	153	154	1	0.015	0.012	1	0.078	0.027
KZDD-047	154	156	2	0.014	<0.005	<1	<0.005	0.0165
KZDD-047	156	158	2	0.013	<0.005	<1	<0.005	0.0155
KZDD-047	158	160	2	0.023	<0.005	<1	<0.005	0.0255
KZDD-047	160	162	2	0.024	<0.005	<1	<0.005	0.0265
KZDD-047	162	164	2	0.016	<0.005	<1	<0.005	0.0185
KZDD-047	164	201	37	Not sampled				
KZDD-047	201	203	2	0.016	0.005	<1	<0.005	0.021
KZDD-047	203	205	2	0.012	<0.005	1	<0.005	0.0145
KZDD-047	205	207	2	0.013	0.005	<1	<0.005	0.018
KZDD-047	207	209	2	0.016	<0.005	<1	0.005	0.0185
KZDD-047	209	211	2	0.009	<0.005	<1	<0.005	0.0115
KZDD-047	211	211.7	0.7	0.026	0.014	<1	0.023	0.04
KZDD-047	211.7	212.2	0.5	0.29	0.435	3	0.178	0.725
KZDD-047	212.2	213	0.8	0.032	0.034	<1	0.057	0.066
KZDD-047	213	213.5	0.5	0.266	0.151	1	0.032	0.417
KZDD-047	213.5	215	1.5	0.014	<0.005	<1	<0.005	0.0165
KZDD-047	215	217	2	0.007	<0.005	<1	0.005	0.0095
KZDD-047	217	219	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-047	219	221	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-047	221	223	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-047	223	225	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-047	225	227	2	0.007	<0.005	<1	0.005	0.0095
KZDD-047	227	229	2	0.015	<0.005	<1	<0.005	0.0175
KZDD-047	229	231	2	0.013	<0.005	<1	<0.005	0.0155
KZDD-047	231	233	2	0.015	<0.005	<1	<0.005	0.0175
KZDD-047	233	235	2	0.017	0.009	<1	0.016	0.026
KZDD-047	235	236	1	0.038	0.04	<1	0.014	0.078
KZDD-047	236	238	2	0.025	0.017	<1	0.015	0.042
KZDD-047	238	239	1	1.145	0.725	8	0.317	1.87
KZDD-047	239	240	1	0.976	0.527	5	0.334	1.503
KZDD-047	240	241	1	0.05	0.122	1	0.245	0.172
KZDD-047	241	242	1	0.357	0.544	6	0.338	0.901
KZDD-047	242	243	1	0.215	0.273	2	0.152	0.488
KZDD-047	243	244	1	1.22	0.591	7	0.217	1.811
KZDD-047	244	245	1	1.21	0.525	5	0.391	1.735
KZDD-047	245	247	2	0.054	0.027	<1	0.025	0.081
KZDD-047	247	249	2	0.017	<0.005	<1	<0.005	0.0195
KZDD-047	249	251	2	0.031	0.01	<1	<0.005	0.041
KZDD-047	251	253	2	0.454	0.225	3	0.066	0.679
KZDD-047	253	254	1	0.363	0.396	4	0.129	0.759
KZDD-047	254	255	1	0.079	0.052	<1	0.058	0.131
KZDD-047	255	257	2	0.009	<0.005	1	<0.005	0.0115
KZDD-047	257	259	2	0.04	0.022	<1	0.011	0.062
KZDD-047	259	260	1	0.241	0.297	4	0.078	0.538
KZDD-047	260	261	1	0.127	0.074	1	0.031	0.201
KZDD-047	261	262	1	0.032	0.011	<1	0.012	0.043
KZDD-047	262	264	2	0.022	0.008	<1	0.019	0.03
KZDD-047	264	266	2	0.032	0.012	1	0.008	0.044
KZDD-047	266	268	2	0.052	0.025	1	0.008	0.077
KZDD-047	268	270	2	0.106	0.052	<1	0.06	0.158
KZDD-047	270	272	2	0.021	0.005	<1	0.012	0.026
KZDD-047	272	300	28	Not sampled				
KZDD-048	0	19	19	Not sampled				



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-048	19	21	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-048	21	23	2	0.007	<0.005	<1	0.008	0.0095
KZDD-048	23	25	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-048	25	27	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-048	27	29	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-048	29	30	1	1.8	0.498	5	0.044	2.298
KZDD-048	30	31	1	1.245	0.749	9	0.076	1.994
KZDD-048	31	32	1	1.06	0.426	5	0.066	1.486
KZDD-048	32	33	1	4.19	2.25	21	0.166	6.44
KZDD-048	33	34	1	2.16	0.926	12	0.153	3.086
KZDD-048	34	34.7	0.7	4.15	1.515	19	0.094	5.665
KZDD-048	34.7	36	1.3	0.192	0.126	2	0.024	0.318
KZDD-048	36	38	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-048	38	39	1	0.574	0.263	2	0.028	0.837
KZDD-048	39	40	1	1.15	0.52	3	0.034	1.67
KZDD-048	40	41	1	3.56	3.23	25	0.043	6.79
KZDD-048	41	42	1	0.544	0.349	2	0.024	0.893
KZDD-048	42	43	1	0.479	0.308	1	0.006	0.787
KZDD-048	43	44	1	0.799	0.328	3	0.025	1.127
KZDD-048	44	45	1	0.377	0.2	<1	0.011	0.577
KZDD-048	45	47	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-048	47	49	2	0.011	<0.005	<1	0.005	0.0135
KZDD-048	49	51	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-048	51	53	2	0.017	0.005	<1	<0.005	0.022
KZDD-048	53	54	1	0.051	0.025	<1	0.023	0.076
KZDD-048	54	55	1	0.283	0.154	2	0.046	0.437
KZDD-048	55	56	1	0.063	0.036	<1	0.008	0.099
KZDD-048	56	57	1	0.022	0.021	<1	0.016	0.043
KZDD-048	57	58	1	0.046	0.019	<1	0.033	0.065
KZDD-048	58	59	1	0.191	0.088	<1	0.025	0.279
KZDD-048	59	61	2	0.131	0.087	<1	0.036	0.218
KZDD-048	61	62	1	1.265	0.517	7	0.312	1.782
KZDD-048	62	63	1	0.029	0.015	<1	0.02	0.044
KZDD-048	63	65	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-048	65	67	2	<0.005	<0.005	<1	0.007	0.0065
KZDD-048	67	69	2	<0.005	<0.005	<1	0.006	0.0065
KZDD-048	69	71	2	<0.005	<0.005	<1	<0.005	0.0065
KZDD-048	71	73	2	0.005	<0.005	<1	<0.005	0.0075
KZDD-048	73	192.1	119.1	Not sampled				
KZDD-048	192.1	194.1	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-048	194.1	194.6	0.5	0.013	<0.005	11	0.012	0.0155
KZDD-048	194.6	196.6	2	0.006	<0.005	<1	<0.005	0.0085
KZDD-049	0	2	2	0.048	<0.005	<1	<0.005	0.0505
KZDD-049	2	4	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-049	4	6	2	0.023	<0.005	<1	<0.005	0.0255
KZDD-049	6	8	2	0.019	<0.005	<1	<0.005	0.0215
KZDD-049	8	9	1	0.045	0.009	<1	<0.005	0.054
KZDD-049	9	11	2	0.013	<0.005	<1	<0.005	0.0155
KZDD-049	11	11.6	0.6	0.009	<0.005	<1	<0.005	0.0115
KZDD-049	11.6	13	1.4	0.008	<0.005	<1	<0.005	0.0105
KZDD-049	13	15	2	0.013	<0.005	<1	0.031	0.0155
KZDD-049	15	17	2	0.01	<0.005	<1	0.016	0.0125
KZDD-049	17	19	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-049	19	21	2	0.01	<0.005	<1	<0.005	0.0125
KZDD-049	21	23	2	0.012	<0.005	<1	0.009	0.0145
KZDD-049	23	23.5	0.5	1.04	0.529	4	0.355	1.569



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-049	23.5	24	0.5	0.476	0.113	<1	0.222	0.589
KZDD-049	24	26	2	0.209	0.13	1	0.012	0.339
KZDD-049	26	28	2	0.789	0.468	4	0.027	1.257
KZDD-049	28	29	1	0.671	0.36	4	0.03	1.031
KZDD-049	29	30	1	0.48	0.228	1	0.043	0.708
KZDD-049	30	31	1	0.433	0.218	2	0.019	0.651
KZDD-049	31	32	1	1.39	0.715	6	0.034	2.105
KZDD-049	32	33.1	1.1	1.18	0.652	4	0.031	1.832
KZDD-049	33.1	35.6	2.5	0.262	0.146	<1	<0.005	0.408
KZDD-049	35.6	37.2	1.6	0.013	<0.005	<1	<0.005	0.0155
KZDD-049	37.2	38	0.8	1.145	0.479	4	0.009	1.624
KZDD-049	38	39	1	0.02	0.012	<1	<0.005	0.032
KZDD-049	39	40	1	0.299	0.126	<1	0.007	0.425
KZDD-049	40	40.9	0.9	2.02	0.878	7	0.008	2.898
KZDD-049	40.9	41.5	0.6	0.332	0.148	1	0.019	0.48
KZDD-049	41.5	42	0.5	20.3	1.53	20	0.173	21.83
KZDD-049	42	43	1	1.725	0.277	4	0.034	2.002
KZDD-049	43	44	1	0.478	0.197	2	0.006	0.675
KZDD-049	44	45	1	0.58	0.12	2	0.013	0.7
KZDD-049	45	46	1	0.049	0.026	1	0.01	0.075
KZDD-049	46	47	1	0.032	0.009	<1	0.005	0.041
KZDD-049	47	49	2	0.063	0.027	<1	0.005	0.09
KZDD-049	49	51	2	0.01	<0.005	<1	0.005	0.0125
KZDD-049	51	52	1	0.013	<0.005	1	<0.005	0.0155
KZDD-049	52	53	1	0.035	0.021	1	0.009	0.056
KZDD-049	53	55	2	0.037	0.016	<1	0.014	0.053
KZDD-049	55	56	1	0.396	0.212	3	0.053	0.608
KZDD-049	56	57	1	0.662	0.352	6	0.09	1.014
KZDD-049	57	58	1	1.8	0.727	10	0.183	2.527
KZDD-049	58	60	2	0.047	0.034	1	0.035	0.081
KZDD-049	60	62	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-049	62	64	2	0.006	<0.005	<1	0.006	0.0085
KZDD-049	64	66	2	0.007	<0.005	<1	<0.005	0.0095
KZDD-049	66	68	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-049	68	150.7	82.7	Not sampled				
KZDD-051	0	3.9	3.9	Not sampled				
KZDD-051	3.9	5.9	2	0.476	0.452	9	0.103	0.928
KZDD-051	5.9	7	1.1	0.124	0.344	6	0.206	0.468
KZDD-051	7	8	1	0.875	0.644	12	0.283	1.519
KZDD-051	8	9	1	0.987	0.925	13	0.23	1.912
KZDD-051	9	9.9	0.9	1.815	1.255	33	1.05	3.07
KZDD-051	9.9	11.6	1.7	6.54	8.32	103	0.543	14.86
KZDD-051	11.6	12.2	0.6	1.03	0.621	10	0.156	1.651
KZDD-051	12.2	13	0.8	3.36	2	46	0.66	5.36
KZDD-051	13	14	1	4.08	1.915	38	0.626	5.995
KZDD-051	14	15	1	5.34	1.165	22	0.614	6.505
KZDD-051	15	16	1	4.28	1.27	22	0.497	5.55
KZDD-051	16	17	1	0.521	0.166	3	0.06	0.687
KZDD-051	17	18	1	0.159	0.099	2	0.009	0.258
KZDD-051	18	19	1	3.37	1.285	14	0.122	4.655
KZDD-051	19	20	1	0.697	0.349	4	0.031	1.046
KZDD-051	20	20.9	0.9	0.304	0.167	4	0.028	0.471
KZDD-051	20.9	22	1.1	0.679	0.325	5	0.07	1.004
KZDD-051	22	23	1	0.446	0.202	4	0.112	0.648
KZDD-051	23	24	1	0.148	0.087	<1	0.021	0.235
KZDD-051	24	25	1	0.191	0.078	2	0.011	0.269



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
KZDD-051	25	26	1	0.058	0.028	2	0.008	0.086
KZDD-051	26	27	1	0.037	0.031	1	0.006	0.068
KZDD-051	27	28	1	0.938	0.442	6	0.021	1.38
KZDD-051	28	29	1	1.035	0.392	5	0.025	1.427
KZDD-051	29	30	1	0.012	<0.005	1	<0.005	0.0145
KZDD-051	30	31	1	0.02	0.011	1	0.005	0.031
KZDD-051	31	32	1	0.403	0.225	4	0.044	0.628
KZDD-051	32	33	1	0.531	0.247	4	0.027	0.778
KZDD-051	33	34	1	0.348	0.184	4	0.023	0.532
KZDD-051	34	35	1	0.042	0.022	2	0.009	0.064
KZDD-051	35	36	1	0.094	0.037	1	0.036	0.131
KZDD-051	36	37	1	0.08	0.051	1	<0.005	0.131
KZDD-051	37	38	1	0.012	<0.005	<1	<0.005	0.0145
KZDD-051	38	39	1	0.528	0.265	2	0.059	0.793
KZDD-051	39	40	1	0.25	0.204	2	0.023	0.454
KZDD-051	40	41	1	0.727	0.271	2	0.059	0.998
KZDD-051	41	42	1	1.645	0.656	5	0.07	2.301
KZDD-051	42	43	1	1.025	0.216	1	0.059	1.241
KZDD-051	43	44	1	0.52	0.382	3	0.025	0.902
KZDD-051	44	45	1	0.807	0.558	3	0.024	1.365
KZDD-051	45	46	1	1.135	0.651	7	0.059	1.786
KZDD-051	46	47	1	1.885	0.952	10	0.185	2.837
KZDD-051	47	48	1	0.856	0.37	4	0.061	1.226
KZDD-051	48	49	1	0.984	0.403	5	0.017	1.387
KZDD-051	49	50	1	0.013	<0.005	<1	0.007	0.0155
KZDD-051	50	51	1	0.017	0.005	<1	0.006	0.022
KZDD-051	51	52	1	0.181	0.099	<1	0.007	0.28
KZDD-051	52	53	1	2.09	0.873	13	0.089	2.963
KZDD-051	53	54	1	0.457	0.246	1	0.035	0.703
KZDD-051	54	55	1	0.548	0.281	2	0.035	0.829
KZDD-051	55	56	1	0.245	0.146	1	0.01	0.391
KZDD-051	56	57	1	0.982	0.635	6	0.153	1.617
KZDD-051	57	58	1	4.46	1.695	19	0.214	6.155
KZDD-051	58	59	1	14.4	6.62	89	0.234	21.02
KZDD-051	59	60	1	4.09	1.55	21	0.154	5.64
KZDD-051	60	61	1	0.244	0.144	1	0.035	0.388
KZDD-051	61	63	2	0.035	0.014	<1	0.009	0.049
KZDD-051	63	65	2	0.011	<0.005	<1	<0.005	0.0135
KZDD-051	65	67	2	0.006	<0.005	<1	0.029	0.0085
KZDD-051	67	69	2	0.008	<0.005	<1	0.016	0.0105
KZDD-051	69	71	2	0.007	<0.005	<1	0.018	0.0095
KZDD-051	71	73	2	0.006	<0.005	<1	0.009	0.0085
KZDD-051	73	75	2	0.01	<0.005	<1	0.008	0.0125
KZDD-051	75	77	2	0.013	0.005	<1	0.013	0.018
KZDD-051	77	78	1	0.015	0.006	<1	0.02	0.021
KZDD-051	78	79	1	0.018	0.007	<1	0.009	0.025
KZDD-051	79	80	1	0.974	0.726	10	0.21	1.7
KZDD-051	80	81	1	1.74	0.874	12	0.336	2.614
KZDD-051	81	82	1	0.094	0.065	2	0.061	0.159
KZDD-051	82	83	1	0.02	0.006	<1	0.009	0.026
KZDD-051	83	85	2	0.011	<0.005	<1	0.007	0.0135
KZDD-051	85	87	2	0.007	<0.005	<1	0.006	0.0095
KZDD-051	87	89	2	0.006	<0.005	<1	0.007	0.0085
KZDD-051	89	91	2	0.008	<0.005	<1	<0.005	0.0105
KZDD-051	91	93	2	0.011	<0.005	<1	0.005	0.0135
SSDD-006	0	0.9	0.9	Not sampled				



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-006	0.9	1.6	0.7	0.228	0.023	<1	0.066	0.251
SSDD-006	1.6	2.5	0.9	0.403	0.009	<1	0.063	0.412
SSDD-006	2.5	3.5	1	0.271	0.012	<1	0.031	0.283
SSDD-006	3.5	4.5	1	0.116	0.006	<1	0.034	0.122
SSDD-006	4.5	5.4	0.9	0.038	0.021	<1	0.044	0.059
SSDD-006	5.4	6.7	1.3	0.079	0.02	<1	0.031	0.099
SSDD-006	6.7	7	0.3	Not sampled				
SSDD-006	7	7.7	0.7	0.043	0.023	1	0.038	0.066
SSDD-006	7.7	8	0.3	Not sampled				
SSDD-006	8	9	1	0.044	0.018	<1	0.031	0.062
SSDD-006	9	10	1	0.028	0.011	<1	0.053	0.039
SSDD-006	10	11	1	0.058	0.039	<1	0.051	0.097
SSDD-006	11	12	1	0.03	0.019	<1	0.037	0.049
SSDD-006	12	13	1	0.045	0.026	<1	0.035	0.071
SSDD-006	13	15	2	0.016	0.006	<1	0.027	0.022
SSDD-006	15	17	2	0.018	0.006	<1	0.024	0.024
SSDD-006	17	18	1	0.016	<0.005	<1	0.024	0.0185
SSDD-006	18	19	1	0.02	<0.005	<1	0.028	0.0225
SSDD-006	19	20	1	0.032	0.01	<1	0.026	0.042
SSDD-006	20	21	1	0.022	<0.005	<1	0.03	0.0245
SSDD-006	21	22	1	0.019	0.006	<1	0.038	0.025
SSDD-006	22	23	1	0.026	0.007	<1	0.028	0.033
SSDD-006	23	24	1	0.009	0.007	<1	0.022	0.016
SSDD-006	24	25	1	0.019	0.011	<1	0.041	0.03
SSDD-006	25	26	1	0.015	0.015	<1	0.026	0.03
SSDD-006	26	27	1	0.023	0.023	<1	0.048	0.046
SSDD-006	27	28	1	0.31	0.884	12	0.049	1.194
SSDD-006	28	29	1	0.013	0.01	<1	0.026	0.023
SSDD-006	29	31	2	0.017	<0.005	<1	0.013	0.0195
SSDD-006	31	32	1	0.015	0.007	<1	0.027	0.022
SSDD-006	32	33	1	0.023	0.012	<1	0.035	0.035
SSDD-006	33	34	1	0.026	0.01	2	0.045	0.036
SSDD-006	34	35	1	0.026	0.007	<1	0.035	0.033
SSDD-006	35	36	1	0.055	0.018	1	0.04	0.073
SSDD-006	36	37	1	0.029	0.011	<1	0.052	0.04
SSDD-006	37	38	1	0.017	0.009	<1	0.06	0.026
SSDD-006	38	38.7	0.7	0.053	0.045	<1	0.037	0.098
SSDD-006	38.7	39.2	0.5	0.438	0.536	2	0.043	0.974
SSDD-006	39.2	40	0.8	0.022	0.007	1	0.038	0.029
SSDD-006	40	41	1	0.025	0.006	<1	0.038	0.031
SSDD-006	41	42	1	0.041	0.023	<1	0.042	0.064
SSDD-006	42	43	1	0.021	0.005	<1	0.029	0.026
SSDD-006	43	44	1	0.019	0.009	<1	0.052	0.028
SSDD-006	44	45	1	0.027	0.01	<1	0.061	0.037
SSDD-006	45	46	1	0.022	0.009	<1	0.079	0.031
SSDD-006	46	47	1	0.023	0.011	<1	0.12	0.034
SSDD-006	47	48	1	0.021	0.017	<1	0.084	0.038
SSDD-006	48	49	1	0.029	0.011	<1	0.115	0.04
SSDD-006	49	50	1	0.019	0.012	<1	0.099	0.031
SSDD-006	50	51	1	0.014	0.007	<1	0.085	0.021
SSDD-006	51	52	1	0.01	<0.005	<1	0.053	0.0125
SSDD-006	52	53	1	0.012	0.006	<1	0.053	0.018
SSDD-006	53	53.5	0.5	0.018	0.01	<1	0.063	0.028
SSDD-006	53.5	54.3	0.8	0.024	0.009	<1	0.09	0.033
SSDD-006	54.3	55.3	1	0.02	0.01	<1	0.064	0.03
SSDD-006	55.3	56	0.7	0.047	0.018	<1	0.115	0.065



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-006	56	57	1	0.021	0.015	<1	0.068	0.036
SSDD-006	57	58	1	0.031	0.008	<1	0.078	0.039
SSDD-006	58	59	1	0.027	0.007	<1	0.061	0.034
SSDD-006	59	60	1	0.028	0.01	<1	0.059	0.038
SSDD-006	60	61	1	0.027	0.009	<1	0.04	0.036
SSDD-006	61	62	1	0.032	0.008	1	0.089	0.04
SSDD-006	62	63	1	0.031	0.008	<1	0.065	0.039
SSDD-006	63	64	1	0.041	0.012	<1	0.071	0.053
SSDD-006	64	65	1	0.032	0.015	<1	0.081	0.047
SSDD-006	65	67	2	0.024	0.014	<1	0.063	0.038
SSDD-006	67	68	1	0.022	0.025	<1	0.065	0.047
SSDD-006	68	69	1	0.046	0.048	1	0.055	0.094
SSDD-006	69	70	1	0.101	0.134	4	0.069	0.235
SSDD-006	70	70.5	0.5	2.15	0.773	14	0.106	2.923
SSDD-006	70.5	71	0.5	8.13	5.18	101	0.214	13.31
SSDD-006	71	72	1	0.143	0.057	1	0.036	0.2
SSDD-006	72	73	1	0.026	0.014	1	0.103	0.04
SSDD-006	73	73.5	0.5	2.42	1.55	27	0.101	3.97
SSDD-006	73.5	74	0.5	0.036	0.077	1	0.028	0.113
SSDD-006	74	74.5	0.5	0.027	0.038	<1	0.033	0.065
SSDD-006	74.5	75.2	0.7	0.039	0.013	<1	0.054	0.052
SSDD-006	75.2	75.7	0.5	0.018	0.02	1	0.036	0.038
SSDD-006	75.7	76.7	1	0.041	0.021	1	0.052	0.062
SSDD-006	76.7	77.4	0.7	0.789	0.077	1	0.067	0.866
SSDD-006	77.4	77.9	0.5	0.021	0.007	1	0.025	0.028
SSDD-006	77.9	79.1	1.2	0.017	0.009	1	0.035	0.026
SSDD-006	79.1	80.6	1.5	0.008	0.005	<1	0.03	0.013
SSDD-006	80.6	81.5	0.9	0.008	<0.005	<1	0.017	0.0105
SSDD-006	81.5	82.5	1	0.01	<0.005	<1	0.072	0.0125
SSDD-006	82.5	84	1.5	0.007	<0.005	<1	0.034	0.0095
SSDD-006	84	85	1	0.005	<0.005	<1	0.033	0.0075
SSDD-006	85	86	1	0.005	0.005	<1	0.027	0.01
SSDD-006	86	87	1	<0.005	<0.005	<1	0.03	0.0065
SSDD-006	87	88	1	0.007	<0.005	<1	0.024	0.0095
SSDD-006	88	89	1	0.005	<0.005	<1	0.035	0.0075
SSDD-006	89	90	1	0.006	<0.005	<1	0.024	0.0085
SSDD-006	90	91	1	0.01	<0.005	<1	0.015	0.0125
SSDD-006	91	92	1	0.01	0.006	<1	0.106	0.016
SSDD-006	92	93	1	0.007	<0.005	<1	0.124	0.0095
SSDD-006	93	94	1	0.007	0.005	<1	0.01	0.012
SSDD-006	94	95	1	0.01	<0.005	<1	0.01	0.0125
SSDD-006	95	96	1	0.01	0.006	<1	0.02	0.016
SSDD-006	96	97.5	1.5	0.006	<0.005	<1	0.01	0.0085
SSDD-006	97.5	99	1.5	0.005	<0.005	<1	0.008	0.0075
SSDD-006	99	101	2	0.01	<0.005	<1	0.013	0.0125
SSDD-006	101	103	2	0.005	<0.005	<1	0.016	0.0075
SSDD-006	103	105	2	0.011	<0.005	<1	0.009	0.0135
SSDD-006	105	107	2	0.01	0.006	<1	0.007	0.016
SSDD-006	107	109	2	0.014	0.009	<1	0.011	0.023
SSDD-006	109	111	2	0.014	0.013	<1	0.006	0.027
SSDD-006	111	113	2	0.006	<0.005	<1	0.01	0.0085
SSDD-006	113	114	1	<0.005	<0.005	<1	0.024	0.0065
SSDD-006	114	115	1	0.011	0.006	<1	0.029	0.017
SSDD-006	115	116	1	0.018	<0.005	<1	0.016	0.0205
SSDD-006	116	117	1	<0.005	<0.005	<1	0.032	<0.005
SSDD-006	117	117.2	0.2	Not sampled				



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-006	117.2	118.1	0.9	0.109	0.058	<1	0.031	0.167
SSDD-006	118.1	119	0.9	0.008	0.007	<1	0.018	0.015
SSDD-006	119	120	1	0.005	<0.005	<1	0.026	0.0075
SSDD-006	120	121	1	0.005	<0.005	<1	0.018	0.0075
SSDD-006	121	122	1	0.018	<0.005	<1	0.019	0.0205
SSDD-006	122	122.5	0.5	<0.005	0.005	<1	0.035	0.009
SSDD-006	122.5	123	0.5	1.68	0.451	7	0.07	2.131
SSDD-006	123	124	1	<0.005	0.005	<1	0.035	0.009
SSDD-006	124	124.7	0.7	0.095	0.046	2	0.022	0.141
SSDD-006	124.7	125.5	0.8	0.039	0.037	<1	0.033	0.076
SSDD-006	125.5	126.2	0.7	0.09	0.044	<1	0.017	0.134
SSDD-006	126.2	126.7	0.5	2.13	1.52	24	0.11	3.65
SSDD-006	126.7	127.6	0.9	0.2	0.028	1	0.023	0.228
SSDD-006	127.6	128.3	0.7	0.005	0.005	<1	0.014	0.01
SSDD-006	128.3	128.8	0.5	0.012	0.01	1	0.011	0.022
SSDD-006	128.8	129.5	0.7	0.934	0.414	6	0.183	1.348
SSDD-006	129.5	130	0.5	12.6	1.475	25	0.367	14.075
SSDD-006	130	131	1	11.05	3.79	62	0.264	14.84
SSDD-006	131	131.7	0.7	3.52	1.52	26	0.129	5.04
SSDD-006	131.7	132.3	0.6	3.91	1.575	26	0.192	5.485
SSDD-006	132.3	133	0.7	0.193	0.107	<1	0.037	0.3
SSDD-006	133	134	1	0.81	0.325	4	0.047	1.135
SSDD-006	134	134.7	0.7	0.375	0.236	3	0.04	0.611
SSDD-006	134.7	135.3	0.6	7.38	5.44	103	0.518	12.82
SSDD-006	135.3	136.1	0.8	9.18	5.88	116	0.541	15.06
SSDD-006	136.1	137	0.9	1.075	0.429	9	0.051	1.504
SSDD-006	137	137.5	0.5	21.1	3.29	64	0.285	24.39
SSDD-006	137.5	138.3	0.8	13.45	7.28	138	0.463	20.73
SSDD-006	138.3	139	0.7	0.104	0.06	<1	0.039	0.164
SSDD-006	139	140	1	0.184	0.082	2	0.045	0.266
SSDD-006	140	141	1	0.03	0.02	<1	0.032	0.05
SSDD-006	141	142	1	0.035	0.038	<1	0.031	0.073
SSDD-006	142	144	2	0.018	0.012	<1	0.02	0.03
SSDD-006	144	146	2	<0.005	<0.005	<1	0.01	0.0065
SSDD-006	146	148	2	0.115	0.034	<1	0.012	0.149
SSDD-006	148	149	1	0.007	0.009	<1	0.009	0.016
SSDD-006	149	150	1	0.284	0.146	2	0.018	0.43
SSDD-006	150	151	1	0.139	0.062	1	0.019	0.201
SSDD-006	151	152	1	0.441	0.187	2	0.08	0.628
SSDD-006	152	153	1	0.275	0.388	6	0.023	0.663
SSDD-006	153	153.7	0.7	0.301	0.301	5	0.044	0.602
SSDD-006	153.7	154.5	0.8	0.455	0.954	18	0.071	1.409
SSDD-006	154.5	155	0.5	0.27	0.159	3	0.046	0.429
SSDD-006	155	156	1	0.199	0.169	3	0.056	0.368
SSDD-006	156	157	1	0.552	0.272	3	0.047	0.824
SSDD-006	157	158	1	0.135	0.08	2	0.014	0.215
SSDD-006	158	159	1	0.478	0.131	2	0.026	0.609
SSDD-006	159	160	1	2.55	1.155	14	0.158	3.705
SSDD-006	160	161	1	3.12	1.39	16	0.334	4.51
SSDD-006	161	162	1	1.705	0.958	9	2.04	2.663
SSDD-006	162	163	1	0.741	0.346	3	0.131	1.087
SSDD-006	163	163.8	0.8	0.382	0.164	1	0.053	0.546
SSDD-006	163.8	164.4	0.6	1.155	0.536	7	0.211	1.691
SSDD-006	164.4	165	0.6	6.6	3.44	48	0.494	10.04
SSDD-006	165	166	1	1.45	0.86	12	0.401	2.31
SSDD-006	166	167	1	0.653	0.358	6	0.732	1.011



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-006	167	168	1	0.316	0.173	1	0.02	0.489
SSDD-006	168	169	1	0.532	0.43	4	0.021	0.962
SSDD-006	169	170	1	0.463	0.227	2	0.026	0.69
SSDD-006	170	171	1	0.263	0.152	<1	0.025	0.415
SSDD-006	171	173	2	0.081	0.04	<1	0.014	0.121
SSDD-006	173	175	2	0.048	0.027	<1	0.005	0.075
SSDD-006	175	176.6	1.6	0.302	0.167	1	0.022	0.469
SSDD-006	176.6	177.5	0.9	0.968	0.575	7	0.069	1.543
SSDD-006	177.5	179	1.5	0.394	0.163	1	0.019	0.557
SSDD-006	179	181	2	1.185	1.255	12	0.079	2.44
SSDD-006	181	183	2	0.019	0.018	<1	0.009	0.037
SSDD-006	183	185	2	0.022	0.022	<1	0.007	0.044
SSDD-006	185	187	2	0.303	0.168	2	0.015	0.471
SSDD-006	187	188	1	0.152	0.079	2	0.009	0.231
SSDD-006	188	189	1	0.113	0.063	<1	0.007	0.176
SSDD-006	189	190	1	0.125	0.124	2	0.01	0.249
SSDD-006	190	192	2	0.013	0.023	<1	0.017	0.036
SSDD-006	192	194	2	0.02	0.02	1	0.008	0.04
SSDD-006	194	196	2	0.024	0.015	<1	0.007	0.039
SSDD-006	196	197	1	0.121	0.078	<1	0.017	0.199
SSDD-006	197	198	1	0.032	0.443	9	0.113	0.475
SSDD-006	198	199	1	0.339	0.663	29	1.58	1.002
SSDD-006	199	200	1	0.346	0.318	9	0.132	0.664
SSDD-006	200	201	1	0.43	0.357	8	0.13	0.787
SSDD-006	201	202	1	0.05	0.042	<1	0.006	0.092
SSDD-006	202	203	1	0.05	0.097	2	0.105	0.147
SSDD-006	203	204	1	0.02	0.037	<1	0.08	0.057
SSDD-006	204	205	1	0.01	0.015	<1	0.16	0.025
SSDD-006	205	206	1	0.009	0.07	3	1.115	0.079
SSDD-006	206	207	1	0.015	0.044	<1	0.19	0.059
SSDD-006	207	208	1	0.014	0.155	1	0.308	0.169
SSDD-006	208	209	1	0.011	0.03	1	0.147	0.041
SSDD-006	209	210	1	0.012	0.028	<1	0.368	0.04
SSDD-006	210	211	1	<0.005	0.406	8	0.085	0.41
SSDD-006	211	212	1	0.009	0.303	7	0.18	0.312
SSDD-006	212	213	1	0.03	0.071	1	0.05	0.101
SSDD-006	213	215	2	0.007	<0.005	<1	0.01	0.0095
SSDD-006	215	217	2	0.007	0.007	<1	0.009	0.014
SSDD-006	217	219	2	0.006	<0.005	<1	0.008	0.0085
SSDD-006	219	220	1	0.177	0.778	15	0.071	0.955
SSDD-006	220	221	1	0.17	0.161	3	0.021	0.331
SSDD-006	221	222	1	0.277	0.379	9	0.123	0.656
SSDD-006	222	223	1	0.117	0.213	6	0.074	0.33
SSDD-006	223	224	1	0.31	0.255	6	0.236	0.565
SSDD-006	224	225	1	0.12	0.139	4	0.183	0.259
SSDD-006	225	226	1	0.363	0.307	7	0.146	0.67
SSDD-006	226	227	1	0.118	0.171	5	0.123	0.289
SSDD-006	227	228	1	0.136	0.16	4	0.048	0.296
SSDD-006	228	229	1	0.256	0.693	14	0.957	0.949
SSDD-006	229	230	1	0.2	0.408	12	0.311	0.608
SSDD-006	230	231	1	0.082	0.254	5	0.452	0.336
SSDD-006	231	232	1	0.05	0.176	5	0.135	0.226
SSDD-006	232	233	1	0.036	0.25	5	0.395	0.286
SSDD-006	233	234	1	0.039	0.271	7	0.068	0.31
SSDD-006	234	235	1	0.053	0.13	4	0.101	0.183
SSDD-006	235	236	1	0.006	0.015	1	0.101	0.021



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-006	236	236.9	0.9	0.099	0.042	<1	0.255	0.141
SSDD-006	236.9	237.5	0.6	0.013	0.028	<1	0.14	0.041
SSDD-006	237.5	238.2	0.7	0.017	0.016	<1	0.187	0.033
SSDD-006	238.2	239	0.8	0.073	0.136	1	0.087	0.209
SSDD-006	239	239.9	0.9	6.54	2.15	42	0.824	8.69
SSDD-006	239.9	240.7	0.8	4.77	1.415	35	1.01	6.185
SSDD-006	240.7	241.7	1	1.21	0.452	9	0.573	1.662
SSDD-006	241.7	242.6	0.9	0.078	0.115	4	0.481	0.193
SSDD-006	242.6	243.3	0.7	0.007	0.998	32	0.044	1.005
SSDD-006	243.3	244	0.7	0.09	0.528	16	0.013	0.618
SSDD-006	244	245	1	0.083	0.158	5	0.012	0.241
SSDD-006	245	246	1	0.055	0.501	18	0.082	0.556
SSDD-006	246	247	1	0.041	0.178	7	0.502	0.219
SSDD-006	247	248	1	0.012	0.044	3	0.045	0.056
SSDD-006	248	249	1	0.114	0.142	3	0.123	0.256
SSDD-006	249	250	1	<0.005	0.039	<1	0.115	0.043
SSDD-006	250	251	1	0.068	0.06	2	0.129	0.128
SSDD-006	251	251.6	0.6	0.009	0.024	<1	0.177	0.033
SSDD-006	251.6	253	1.4	0.01	0.021	<1	0.124	0.031
SSDD-006	253	255	2	0.007	0.012	<1	0.015	0.019
SSDD-006	255	256	1	0.011	0.011	1	0.145	0.022
SSDD-006	256	258	2	0.005	0.006	<1	0.008	0.011
SSDD-006	258	260	2	0.009	<0.005	1	0.009	0.0115
SSDD-006	260	262	2	0.007	0.007	1	0.005	0.014
SSDD-006	262	264	2	0.007	<0.005	1	0.007	0.0095
SSDD-006	264	265	1	<0.005	<0.005	2	0.01	<0.005
SSDD-006	265	266	1	<0.005	<0.005	1	0.014	<0.005
SSDD-006	266	267	1	0.006	0.005	<1	0.005	0.011
SSDD-006	267	268	1	0.009	<0.005	<1	0.014	0.0115
SSDD-006	268	269	1	<0.005	<0.005	<1	0.007	0.0065
SSDD-006	269	270	1	<0.005	<0.005	<1	0.009	0.0055
SSDD-006	270	271	1	0.005	<0.005	<1	<0.005	0.0075
SSDD-006	271	272	1	0.018	0.011	<1	0.015	0.029
SSDD-006	272	273	1	<0.005	<0.005	<1	<0.005	0.0065
SSDD-006	273	274	1	<0.005	0.006	<1	0.013	0.01
SSDD-006	274	275	1	<0.005	0.005	<1	0.011	0.009
SSDD-006	275	276	1	<0.005	<0.005	<1	0.006	0.0065
SSDD-006	276	277	1	0.005	<0.005	<1	0.007	0.0075
SSDD-006	277	278	1	0.007	0.01	<1	0.095	0.017
SSDD-006	278	279	1	0.012	<0.005	<1	0.016	0.0145
SSDD-006	279	280	1	0.008	<0.005	1	0.005	0.0105
SSDD-006	280	281	1	0.005	<0.005	<1	0.011	0.0075
SSDD-006	281	282	1	0.009	0.012	<1	0.03	0.021
SSDD-006	282	283	1	0.008	<0.005	<1	0.01	0.0105
SSDD-006	283	284	1	0.008	<0.005	1	0.04	0.0105
SSDD-006	284	285	1	<0.005	<0.005	<1	0.011	0.0065
SSDD-006	285	287	2	0.005	<0.005	<1	0.012	0.0075
SSDD-006	287	287.8	0.8	0.005	<0.005	<1	<0.005	0.0075
SSDD-006	287.8	288.8	1	0.006	<0.005	<1	0.015	0.0085
SSDD-006	288.8	289.7	0.9	0.01	<0.005	<1	0.009	0.0125
SSDD-006	289.7	290.6	0.9	0.007	<0.005	<1	0.021	0.0095
SSDD-006	290.6	292	1.4	<0.005	<0.005	<1	0.014	0.0065
SSDD-006	292	294	2	<0.005	<0.005	<1	0.007	0.0065
SSDD-006	294	296	2	<0.005	<0.005	<1	0.012	0.0055
SSDD-006	296	298	2	0.005	<0.005	<1	0.014	0.0075
SSDD-006	298	300	2	0.006	<0.005	<1	0.007	0.0085



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-006	300	301.3	1.3	0.007	<0.005	1	0.013	0.0095
SSDD-006	301.3	303	1.7	0.016	0.005	3	0.201	0.021
SSDD-006	303	305	2	0.006	<0.005	<1	0.005	0.0085
SSDD-006	305	306	1	0.005	<0.005	<1	0.005	0.0075
SSDD-006	306	307	1	<0.005	<0.005	<1	0.011	0.0065
SSDD-006	307	308	1	0.006	<0.005	<1	0.005	0.0085
SSDD-006	308	309	1	0.005	<0.005	<1	<0.005	0.0075
SSDD-006	309	310	1	<0.005	<0.005	<1	0.013	0.0065
SSDD-006	310	311	1	0.005	<0.005	<1	0.01	0.0075
SSDD-006	311	312	1	0.005	<0.005	<1	0.01	0.0075
SSDD-006	312	313	1	0.008	0.006	<1	0.006	0.014
SSDD-006	313	315	2	0.006	<0.005	<1	0.012	0.0085
SSDD-006	315	316	1	<0.005	<0.005	<1	<0.005	0.0065
SSDD-006	316	318	2	0.007	0.007	<1	0.024	0.014
SSDD-006	318	320	2	0.005	0.005	<1	0.011	0.01
SSDD-006	320	322	2	0.015	0.008	<1	0.008	0.023
SSDD-006	322	324	2	0.016	0.014	<1	0.012	0.03
SSDD-006	324	325	1	0.019	0.018	<1	0.016	0.037
SSDD-006	325	326.6	1.6	0.019	0.018	1	0.014	0.037
SSDD-007	0	0.6	0.6	0.035	3.35	32	0.242	3.385
SSDD-007	0.6	1.6	1	0.135	0.625	3	0.064	0.76
SSDD-007	1.6	2.6	1	0.096	0.252	2	0.067	0.348
SSDD-007	2.6	3.3	0.7	0.079	0.179	2	0.096	0.258
SSDD-007	3.3	3.8	0.5	0.146	0.476	5	0.278	0.622
SSDD-007	3.8	4.6	0.8	3.09	0.14	<1	0.202	3.23
SSDD-007	4.6	5.2	0.6	5.43	0.11	<1	0.035	5.54
SSDD-007	5.2	6	0.8	5.36	0.219	2	0.055	5.579
SSDD-007	6	6.7	0.7	6.75	2.11	32	0.186	8.86
SSDD-007	6.7	7.5	0.8	4.86	1.925	32	0.166	6.785
SSDD-007	7.5	8.2	0.7	1.76	0.598	8	0.09	2.358
SSDD-007	8.2	9.2	1	4.75	1.235	19	0.117	5.985
SSDD-007	9.2	10.2	1	3.86	0.881	14	0.4	4.741
SSDD-007	10.2	11	0.8	29.2	6.67	106	0.658	35.87
SSDD-007	11	11.6	0.6	23.3	4.82	72	0.917	28.12
SSDD-007	11.6	12.5	0.9	2.43	1.23	20	0.142	3.66
SSDD-007	12.5	13	0.5	4.3	2.08	35	0.323	6.38
SSDD-007	13	14	1	2.94	1.42	21	0.115	4.36
SSDD-007	14	15	1	0.565	0.542	9	0.047	1.107
SSDD-007	15	16.8	1.8	0.563	0.266	3	0.037	0.829
SSDD-007	16.8	17.7	0.9	0.163	0.085	4	0.033	0.248
SSDD-007	17.7	18.5	0.8	0.045	0.028	1	0.027	0.073
SSDD-007	18.5	19.5	1	0.083	0.033	<1	0.021	0.116
SSDD-007	19.5	20.5	1	1.17	0.425	7	0.039	1.595
SSDD-007	20.5	21.3	0.8	2.85	0.832	14	0.06	3.682
SSDD-007	21.3	22	0.7	21.9	7.46	120	0.709	29.36
SSDD-007	22	23	1	10.65	4.6	70	0.285	15.25
SSDD-007	23	24	1	6.26	2.66	40	0.141	8.92
SSDD-007	24	24.9	0.9	2.27	1.625	25	0.208	3.895
SSDD-007	24.9	25.8	0.9	3.78	1.99	35	0.226	5.77
SSDD-007	25.8	26.8	1	0.259	0.177	3	0.082	0.436
SSDD-007	26.8	27.8	1	0.761	0.651	11	0.127	1.412
SSDD-007	27.8	28.6	0.8	1.8	0.806	12	0.114	2.606
SSDD-007	28.6	29.3	0.7	14.55	10.5	171	0.246	25.05
SSDD-007	29.3	30	0.7	0.347	0.16	6	0.087	0.507
SSDD-007	30	31	1	0.83	0.34	8	0.066	1.17
SSDD-007	31	33	2	0.379	0.178	2	0.155	0.557



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-007	33	35	2	0.098	0.012	1	0.094	0.11
SSDD-007	35	36	1	1.24	0.925	15	0.121	2.165
SSDD-007	36	37	1	0.189	0.121	2	0.081	0.31
SSDD-007	37	38	1	0.266	0.162	3	0.052	0.428
SSDD-007	38	39	1	0.46	0.214	3	0.05	0.674
SSDD-007	39	40	1	0.181	0.009	<1	0.051	0.19
SSDD-007	40	42	2	0.355	0.006	<1	0.059	0.361
SSDD-007	42	44	2	0.163	<0.005	1	0.066	0.1655
SSDD-007	44	46	2	0.178	0.016	<1	0.06	0.194
SSDD-007	46	47.6	1.6	0.417	0.007	<1	0.043	0.424
SSDD-007	47.6	48.5	0.9	0.33	0.021	<1	0.023	0.351
SSDD-007	48.5	50.5	2	0.131	0.006	<1	0.018	0.137
SSDD-007	50.5	51	0.5	0.071	0.017	1	0.048	0.088
SSDD-007	51	53	2	0.055	0.01	<1	0.021	0.065
SSDD-007	53	55	2	0.026	<0.005	<1	0.03	0.0285
SSDD-007	55	56	1	0.048	0.038	1	0.03	0.086
SSDD-007	56	56.7	0.7	3.3	1.755	32	0.203	5.055
SSDD-007	56.7	57.5	0.8	0.288	0.131	5	0.044	0.419
SSDD-007	57.5	58.5	1	0.048	0.023	1	0.069	0.071
SSDD-007	58.5	59.7	1.2	0.027	0.016	2	0.065	0.043
SSDD-007	59.7	60.3	0.6	0.125	0.063	1	0.058	0.188
SSDD-007	60.3	61.3	1	0.087	0.046	1	0.05	0.133
SSDD-007	61.3	62.3	1	0.254	0.123	2	0.083	0.377
SSDD-007	62.3	63.3	1	0.059	0.04	4	0.085	0.099
SSDD-007	63.3	64.1	0.8	12.75	7.07	142	0.772	19.82
SSDD-007	64.1	64.7	0.6	4.73	1.15	22	0.305	5.88
SSDD-007	64.7	65.6	0.9	0.056	0.059	3	0.073	0.115
SSDD-007	65.6	66.6	1	0.147	0.058	<1	0.087	0.205
SSDD-007	66.6	68	1.4	0.059	0.037	<1	0.085	0.096
SSDD-007	68	70	2	0.012	0.005	<1	0.062	0.017
SSDD-007	70	71	1	0.018	0.014	<1	0.069	0.032
SSDD-007	71	71.8	0.8	0.021	0.023	1	0.066	0.044
SSDD-007	71.8	72.4	0.6	0.063	0.033	<1	0.067	0.096
SSDD-007	72.4	73	0.6	0.077	0.042	2	0.051	0.119
SSDD-007	73	73.7	0.7	0.504	0.196	3	0.063	0.7
SSDD-007	73.7	75.2	1.5	0.015	0.022	1	0.024	0.037
SSDD-007	75.2	75.8	0.6	0.391	0.139	1	0.061	0.53
SSDD-007	75.8	77.8	2	0.026	0.021	<1	0.032	0.047
SSDD-007	77.8	79.7	1.9	0.02	0.027	<1	0.028	0.047
SSDD-007	79.7	80.4	0.7	0.262	0.14	<1	0.052	0.402
SSDD-007	80.4	81	0.6	0.068	0.044	<1	0.056	0.112
SSDD-007	81	83	2	0.034	0.013	<1	0.023	0.047
SSDD-007	83	85	2	0.039	0.011	<1	0.034	0.05
SSDD-007	85	86.6	1.6	0.03	0.017	<1	0.042	0.047
SSDD-007	86.6	87.7	1.1	0.038	0.024	<1	0.067	0.062
SSDD-007	87.7	88.5	0.8	0.143	0.02	<1	0.025	0.163
SSDD-007	88.5	90	1.5	0.024	0.017	<1	0.018	0.041
SSDD-007	90	91	1	0.041	0.044	<1	0.018	0.085
SSDD-007	91	93	2	0.047	0.042	1	0.017	0.089
SSDD-007	93	95	2	0.027	0.025	<1	0.022	0.052
SSDD-007	95	97	2	0.031	0.024	<1	0.013	0.055
SSDD-007	97	99	2	0.032	0.024	<1	0.01	0.056
SSDD-007	99	100	1	0.044	0.027	1	0.014	0.071
SSDD-007	100	101	1	0.027	0.02	<1	0.016	0.047
SSDD-007	101	103	2	0.039	0.022	<1	0.016	0.061
SSDD-007	103	105	2	0.039	0.026	<1	0.016	0.065



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-007	105	107	2	0.04	0.018	1	0.02	0.058
SSDD-007	107	108.9	1.9	0.014	0.018	<1	0.029	0.032
SSDD-007	108.9	109.7	0.8	0.127	0.187	1	0.032	0.314
SSDD-007	109.7	110.4	0.7	0.292	0.095	<1	0.056	0.387
SSDD-007	110.4	111.2	0.8	0.017	0.024	1	0.02	0.041
SSDD-007	111.2	112.2	1	0.022	0.043	<1	0.038	0.065
SSDD-007	112.2	112.8	0.6	0.586	0.486	2	0.061	1.072
SSDD-007	112.8	113.7	0.9	0.072	0.032	<1	0.053	0.104
SSDD-007	113.7	114.5	0.8	0.061	0.03	<1	0.064	0.091
SSDD-007	114.5	116.4	1.9	0.03	0.023	<1	0.048	0.053
SSDD-007	116.4	117	0.6	0.016	0.027	<1	0.037	0.043
SSDD-007	117	118	1	0.024	0.023	<1	0.042	0.047
SSDD-007	118	120	2	0.021	0.024	<1	0.03	0.045
SSDD-007	120	122	2	0.044	0.026	<1	0.054	0.07
SSDD-007	122	123	1	0.033	0.028	1	0.045	0.061
SSDD-007	123	124	1	0.043	0.018	<1	0.046	0.061
SSDD-007	124	126	2	0.024	0.009	<1	0.027	0.033
SSDD-007	126	128	2	0.01	<0.005	<1	0.037	0.0125
SSDD-007	128	130	2	0.018	0.006	<1	0.025	0.024
SSDD-007	130	132	2	0.012	0.006	<1	0.015	0.018
SSDD-007	132	134	2	0.02	0.005	<1	0.02	0.025
SSDD-007	134	136	2	0.018	0.008	<1	0.014	0.026
SSDD-007	136	138	2	0.027	0.006	<1	0.032	0.033
SSDD-007	138	140	2	0.02	0.007	<1	0.023	0.027
SSDD-007	140	142	2	0.041	0.023	<1	0.03	0.064
SSDD-007	142	144	2	0.022	0.009	<1	0.058	0.031
SSDD-007	144	145	1	0.032	0.028	2	0.064	0.06
SSDD-007	145	145.9	0.9	1.935	0.996	18	0.11	2.931
SSDD-007	145.9	146.5	0.6	20.2	17.2	298	0.192	37.4
SSDD-007	146.5	147.2	0.7	1.25	0.449	8	0.131	1.699
SSDD-007	147.2	149	1.8	0.152	0.125	3	0.064	0.277
SSDD-007	149	150.3	1.3	0.041	0.025	<1	0.043	0.066
SSDD-007	150.3	151	0.7	0.055	0.065	1	0.046	0.12
SSDD-007	151	153	2	0.071	0.023	1	0.046	0.094
SSDD-007	153	154	1	0.16	0.082	1	0.027	0.242
SSDD-007	154	154.8	0.8	0.462	0.239	4	0.069	0.701
SSDD-007	154.8	155.4	0.6	13.8	12.45	240	0.229	26.25
SSDD-007	155.4	156.2	0.8	0.063	0.032	1	0.036	0.095
SSDD-007	156.2	157	0.8	0.697	0.18	4	0.06	0.877
SSDD-007	157	158	1	0.016	0.006	<1	0.009	0.022
SSDD-007	158	160	2	0.006	<0.005	<1	0.011	0.0085
SSDD-007	160	162	2	0.008	<0.005	<1	0.016	0.0105
SSDD-007	162	164	2	0.009	0.007	<1	0.04	0.016
SSDD-007	164	166	2	<0.005	<0.005	1	0.053	0.0065
SSDD-007	166	167	1	0.007	0.006	<1	0.042	0.013
SSDD-007	167	168	1	0.183	0.051	1	0.011	0.234
SSDD-007	168	169	1	0.009	<0.005	<1	<0.005	0.0115
SSDD-007	169	171	2	0.005	<0.005	<1	<0.005	0.0075
SSDD-007	171	173	2	0.007	0.005	<1	0.047	0.012
SSDD-007	173	175	2	0.011	0.011	<1	0.012	0.022
SSDD-007	175	176	1	0.006	<0.005	1	0.009	0.0085
SSDD-007	176	176.8	0.8	0.006	<0.005	<1	0.017	0.0085
SSDD-007	176.8	178.4	1.6	<0.005	<0.005	<1	0.007	0.0065
SSDD-007	178.4	179.6	1.2	<0.005	<0.005	<1	0.008	0.0065
SSDD-007	179.6	181.6	2	0.005	<0.005	<1	0.011	0.0075
SSDD-007	181.6	183	1.4	0.01	0.006	<1	0.007	0.016



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-007	183	184	1	0.411	0.196	4	0.05	0.607
SSDD-007	184	185	1	0.056	0.035	1	0.018	0.091
SSDD-007	185	185.7	0.7	0.154	0.084	2	0.056	0.238
SSDD-007	185.7	186.6	0.9	0.426	0.193	4	0.036	0.619
SSDD-007	186.6	187.5	0.9	0.512	0.481	11	0.053	0.993
SSDD-007	187.5	188.5	1	0.123	0.064	1	0.021	0.187
SSDD-007	188.5	189.5	1	0.292	0.142	3	0.03	0.434
SSDD-007	189.5	190.1	0.6	1.115	0.348	6	0.103	1.463
SSDD-007	190.1	191	0.9	0.43	0.171	4	0.06	0.601
SSDD-007	191	192	1	1.575	0.457	8	0.317	2.032
SSDD-007	192	193	1	1.96	0.636	11	0.118	2.596
SSDD-007	193	194.7	1.7	0.265	0.136	3	0.025	0.401
SSDD-007	194.7	195.2	0.5	0.519	0.262	4	0.044	0.781
SSDD-007	195.2	197	1.8	0.172	0.103	2	0.015	0.275
SSDD-007	197	198	1	0.498	0.263	2	0.043	0.761
SSDD-007	198	198.5	0.5	1.095	0.527	5	0.101	1.622
SSDD-007	198.5	199.3	0.8	0.5	0.303	2	0.039	0.803
SSDD-007	199.3	200.3	1	2.58	1.645	15	1.9	4.225
SSDD-007	200.3	201.3	1	0.723	0.391	4	0.13	1.114
SSDD-007	201.3	202.2	0.9	1.415	0.958	14	0.102	2.373
SSDD-007	202.2	203	0.8	1.23	0.725	14	0.05	1.955
SSDD-007	203	204	1	1.625	1.05	27	0.232	2.675
SSDD-007	204	205	1	1.005	0.584	12	0.072	1.589
SSDD-007	205	206	1	1.29	0.644	10	0.049	1.934
SSDD-007	206	207	1	0.831	0.539	8	0.036	1.37
SSDD-007	207	209	2	0.283	0.181	4	0.041	0.464
SSDD-007	209	210	1	0.553	0.559	10	0.092	1.112
SSDD-007	210	210.7	0.7	0.552	0.275	5	1.065	0.827
SSDD-007	210.7	211.3	0.6	2.52	0.75	16	1.575	3.27
SSDD-007	211.3	212	0.7	0.145	0.168	3	3.1	0.313
SSDD-007	212	212.8	0.8	3.49	1.805	33	0.05	5.295
SSDD-007	212.8	213.4	0.6	2.69	1.705	31	1.18	4.395
SSDD-007	213.4	214	0.6	0.512	0.592	11	0.358	1.104
SSDD-007	214	214.7	0.7	1.285	0.703	16	0.217	1.988
SSDD-007	214.7	215.7	1	0.351	0.477	12	0.047	0.828
SSDD-007	215.7	216.3	0.6	0.517	0.499	12	0.177	1.016
SSDD-007	216.3	217.3	1	0.122	0.085	2	0.032	0.207
SSDD-007	217.3	217.9	0.6	0.532	0.389	9	0.053	0.921
SSDD-007	217.9	218.5	0.6	0.397	1.355	31	0.981	1.752
SSDD-007	218.5	219.5	1	0.461	0.368	10	0.062	0.829
SSDD-007	219.5	220.5	1	0.193	2.3	87	0.757	2.493
SSDD-007	220.5	221	0.5	0.095	0.156	3	0.08	0.251
SSDD-007	221	222	1	0.179	0.188	3	0.059	0.367
SSDD-007	222	223	1	0.274	0.301	8	0.045	0.575
SSDD-007	223	224	1	0.397	0.686	17	0.28	1.083
SSDD-007	224	225	1	0.093	0.12	2	0.02	0.213
SSDD-007	225	226	1	0.362	0.441	11	0.073	0.803
SSDD-007	226	227	1	0.005	0.007	<1	0.011	0.012
SSDD-007	227	229	2	0.013	0.015	<1	0.009	0.028
SSDD-007	229	231	2	0.085	0.107	2	0.035	0.192
SSDD-007	231	233	2	0.036	0.017	<1	0.022	0.053
SSDD-007	233	235	2	0.044	0.041	1	0.025	0.085
SSDD-007	235	237	2	0.027	0.059	2	0.026	0.086
SSDD-007	237	239	2	0.073	0.132	1	0.022	0.205
SSDD-007	239	239.6	0.6	0.045	0.021	<1	0.011	0.066
SSDD-007	239.6	240.2	0.6	0.36	0.436	8	0.073	0.796



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-007	240.2	241	0.8	0.158	0.111	3	0.017	0.269
SSDD-007	241	242	1	0.101	0.078	3	0.016	0.179
SSDD-007	242	242.8	0.8	0.417	0.835	22	0.576	1.252
SSDD-007	242.8	243.4	0.6	0.082	0.504	15	0.05	0.586
SSDD-007	243.4	244	0.6	0.11	0.649	17	0.096	0.759
SSDD-007	244	244.6	0.6	0.349	0.565	15	0.465	0.914
SSDD-007	244.6	245.2	0.6	1.245	1.57	46	6.02	2.815
SSDD-007	245.2	246	0.8	0.477	0.412	12	0.177	0.889
SSDD-007	246	247	1	0.185	0.469	13	0.112	0.654
SSDD-007	247	248	1	0.495	0.777	23	0.077	1.272
SSDD-007	248	249	1	0.752	0.564	16	0.031	1.316
SSDD-007	249	250	1	0.559	0.415	11	0.023	0.974
SSDD-007	250	251	1	0.608	0.54	15	0.039	1.148
SSDD-007	251	252	1	0.402	0.289	9	0.032	0.691
SSDD-007	252	252.7	0.7	0.389	0.783	20	0.172	1.172
SSDD-007	252.7	253.3	0.6	0.127	0.156	5	0.101	0.283
SSDD-007	253.3	253.8	0.5	0.658	0.577	18	9	1.235
SSDD-007	253.8	254.8	1	0.473	0.352	9	0.301	0.825
SSDD-007	254.8	255.5	0.7	0.184	0.184	4	0.042	0.368
SSDD-007	255.5	256	0.5	0.406	0.267	6	0.052	0.673
SSDD-007	256	257	1	0.539	0.535	13	0.119	1.074
SSDD-007	257	258	1	0.69	0.513	10	0.029	1.203
SSDD-007	258	259	1	0.625	0.509	7	0.038	1.134
SSDD-007	259	261	2	0.298	0.253	4	0.041	0.551
SSDD-007	261	262	1	0.054	0.046	<1	0.011	0.1
SSDD-007	262	263	1	0.118	0.261	7	0.044	0.379
SSDD-007	263	265	2	0.066	0.067	1	0.015	0.133
SSDD-007	265	266	1	0.044	0.045	1	0.015	0.089
SSDD-007	266	267.5	1.5	0.179	0.115	1	0.02	0.294
SSDD-007	267.5	268.3	0.8	0.398	0.257	3	0.035	0.655
SSDD-007	268.3	269	0.7	0.318	0.11	<1	0.018	0.428
SSDD-007	269	271	2	0.355	0.531	12	0.144	0.886
SSDD-007	271	272	1	0.414	0.472	13	0.059	0.886
SSDD-007	272	273	1	0.145	0.158	5	0.016	0.303
SSDD-007	273	274.1	1.1	0.455	0.313	9	0.033	0.768
SSDD-007	274.1	274.8	0.7	0.394	3.1	69	1.695	3.494
SSDD-007	274.8	275.5	0.7	0.097	3.02	94	0.471	3.117
SSDD-007	275.5	276	0.5	0.669	1.035	29	0.207	1.704
SSDD-007	276	277	1	0.222	0.488	13	0.186	0.71
SSDD-007	277	279	2	0.414	1.065	26	0.074	1.479
SSDD-007	279	280.4	1.4	0.362	0.453	10	0.116	0.815
SSDD-007	280.4	281.3	0.9	0.211	0.192	4	0.05	0.403
SSDD-007	281.3	283	1.7	0.288	0.264	7	0.241	0.552
SSDD-007	283	284.5	1.5	0.182	0.322	8	0.251	0.504
SSDD-007	284.5	285.6	1.1	0.043	0.106	3	0.049	0.149
SSDD-007	285.6	287.6	2	0.041	0.098	2	0.046	0.139
SSDD-007	287.6	289	1.4	0.067	0.153	3	0.043	0.22
SSDD-007	289	291	2	<0.005	<0.005	<1	0.01	0.0065
SSDD-007	291	293	2	0.007	0.04	2	0.031	0.047
SSDD-007	293	295	2	0.005	<0.005	<1	0.012	0.0075
SSDD-007	295	297	2	0.047	0.378	11	0.156	0.425
SSDD-007	297	299	2	0.012	0.099	2	0.041	0.111
SSDD-007	299	301	2	<0.005	<0.005	1	0.016	0.0065
SSDD-007	301	302.2	1.2	0.006	0.032	1	0.032	0.038
SSDD-007	302.2	303.8	1.6	0.016	0.264	10	0.037	0.28
SSDD-007	303.8	305	1.2	0.013	0.022	2	0.034	0.035



Hole ID	From (m)	To (m)	Interval (m)	Zn (%)	Pb (%)	Ag (ppm)	Au (ppm)	Zn+Pb (%)
SSDD-007	305	306	1	0.013	0.023	2	0.048	0.036
SSDD-007	306	308	2	0.007	0.005	<1	0.097	0.012
SSDD-007	308	309.8	1.8	0.015	0.011	<1	0.059	0.026
SSDD-007	309.8	310.8	1	0.026	0.103	4	0.079	0.129
SSDD-007	310.8	312	1.2	<0.005	<0.005	<1	0.008	0.0065
SSDD-007	312	314	2	0.091	0.17	3	0.054	0.261
SSDD-007	314	316	2	0.029	0.025	1	0.029	0.054
SSDD-007	316	317	1	0.007	0.15	7	0.149	0.157
SSDD-007	317	317.5	0.5	0.143	0.029	1	0.786	0.172
SSDD-007	317.5	318	0.5	0.019	0.017	1	0.063	0.036
SSDD-007	318	319	1	0.078	0.092	2	0.032	0.17
SSDD-007	319	321	2	0.061	0.072	2	0.04	0.133
SSDD-007	321	323	2	0.096	0.095	2	0.014	0.191
SSDD-007	323	324	1	0.139	0.119	1	0.008	0.258
SSDD-007	324	326	2	0.084	0.108	2	0.012	0.192
SSDD-007	326	328	2	0.013	0.009	<1	0.007	0.022
SSDD-007	328	330	2	0.017	0.008	1	0.006	0.025
SSDD-007	330	332	2	0.022	0.016	1	0.025	0.038
SSDD-007	332	334	2	0.01	0.005	<1	0.031	0.015
SSDD-007	334	336	2	0.006	<0.005	<1	0.026	0.0085
SSDD-007	336	338	2	0.007	<0.005	<1	0.007	0.0095
SSDD-007	338	338.7	0.7	0.006	<0.005	<1	0.009	0.0085
SSDD-007	338.7	339.2	0.5	0.005	<0.005	<1	0.098	0.0075
SSDD-007	339.2	340	0.8	0.008	<0.005	1	0.027	0.0105
SSDD-007	340	341	1	0.006	<0.005	<1	0.014	0.0085
SSDD-007	341	342	1	0.006	<0.005	1	<0.005	0.0085
SSDD-007	342	343	1	0.006	<0.005	<1	0.007	0.0085
SSDD-007	343	345	2	0.005	<0.005	<1	<0.005	0.0075
SSDD-007	345	347	2	0.007	<0.005	<1	0.005	0.0095
SSDD-007	347	349	2	0.007	<0.005	<1	0.006	0.0095
SSDD-007	349	350	1	0.008	<0.005	<1	0.009	0.0105
SSDD-007	350	351	1	0.005	<0.005	1	<0.005	0.0075
SSDD-007	351	353	2	0.005	<0.005	<1	<0.005	0.0075
SSDD-007	353	355	2	0.006	<0.005	<1	<0.005	0.0085
SSDD-007	355	357	2	0.006	<0.005	<1	<0.005	0.0085
SSDD-007	357	359	2	0.006	<0.005	<1	0.014	0.0085
SSDD-007	359	361	2	0.006	<0.005	1	0.015	0.0085
SSDD-007	361	362.5	1.5	0.006	<0.005	1	<0.005	0.0085
SSDD-007	362.5	363	0.5	0.007	<0.005	<1	0.031	0.0095
SSDD-007	363	364	1	0.008	<0.005	<1	0.012	0.0105
SSDD-007	364	365.7	1.7	0.007	0.005	1	0.038	0.012



APPENDIX 2: JORC TABLES

Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
Sampling techniques	<i>Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling.</i>	Drill core samples were collected from half cut PQ and HQ diameter core, where the core was sawn exactly in half along a pre-defined cutting line. Sample intervals were determined by the geologist and samples were placed into labelled and tagged sample bags prior to dispatch. A sample tag was also placed in the core box. A specific gravity sample was taken at 10 metre intervals, or at each change in lithology, using whole core prior to cutting and sampling for analysis. Specific gravity was measured using the Archimedes principle.
	<i>Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used.</i>	For drill hole analyses, sample intervals were selected by the logging geologists based on geological criteria including presence of alteration and mineralisation, style of mineralisation and lithological contacts. Minimum sample lengths of 0.5 metres and maximum sample lengths of 2 metres were employed. Each sample weighed between 2 and 13 kg depending on the length of the sample and diameter of drill core. On silver-lead-zinc vein targets, sampling was only conducted on visually mineralised intervals, including 10 metres either side of the visually mineralised interval. On copper-gold porphyry targets, the entire hole was sampled.
	<i>Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</i>	For drill hole analyses, diamond drilling was used to obtain 2 to 13kg samples, prepared at ALS Bor, Serbia. The sample pulps were sent to ALS Rosia Montana, Romania by air freight for gold analysis by 30 gram fire assay with AA finish (code FA-AA23), and multi-element analyses were conducted by ALS Loughrea, Ireland using a highly oxidising digestion with ICP-MS finish (code ME-ICPORE).
Drilling techniques	<i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i>	All holes were drilled by coring producing PQ and HQ diameter core and recovered using triple tube. Downhole surveys were recorded by the drillers every 30m downhole and at the end of each hole using a Reflex EZ-trac tool. Core was oriented a Reflex tool.
Drill sample recovery	<i>Method of recording and assessing core and chip sample recoveries and results assessed.</i>	All core was geotechnically logged to verify drillers blocks, record the run length, recovered length, core recovery (%), RQD and fracture index. Core recovery was maximised through drilling shorter drill runs in friable zones and zones of water loss. There is no observed relationship between sample recovery and grade.
	<i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i>	
	<i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i>	
Logging	<i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i>	Core samples were geologically logged to a level of detail that would support appropriate Mineral Resource estimation, mining and metallurgical studies. Basic geotechnical logging (RQD, fracture index, core recovery) was recorded and is sufficient for Mineral Resource estimation. Additional geotechnical logging would be required for mining studies. Core logging is qualitative and all core is photographed. All of the core (100%) is logged.
	<i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i>	



Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
	<i>The total length and percentage of the relevant intersections logged.</i>	
Sub-sampling techniques and sample preparation	<i>If core, whether cut or sawn and whether quarter, half or all core taken.</i>	Core samples were sawn exactly in half.
	<i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i>	Not applicable, as all samples are core.
	<i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i>	Collection of around 2-13kg of half core material with subsequent pulverisation of the total charge provided an appropriate and representative sample for analysis. Sample preparation was undertaken at the ALS laboratory in Bor, to industry best practice.
	<i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i>	Industry best practice was adopted by ALS for laboratory sub-sampling and the avoidance of any cross contamination. Adriatic inserted blind blanks at a rate of one per batch of 20 samples, typically sequentially following a mineralised sample.
	<i>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</i>	At Kizevak, two composite samples were collected from mineralised quarter cut core, and were prepared and analysed at MMI Bor. Comparison between the exploration assays and the MMI Bor and drill assay results demonstrate that sampling is representative of the in-situ material collected. Adriatic routinely assay pulp duplicates which show excellent repeatability ($R > 0.9$). Adriatic also collect half core duplicate samples in every third batch.
	<i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i>	Sample size of 2-13 kg is appropriate to the grain size of the material being tested.
Quality of assay data and laboratory tests	<i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i>	The sample pulps were sent to ALS Rosia Montana, Romania by air freight for gold analysis by 30-gram fire assay with AA finish (code FA-AA23). Multi-element analyses were conducted by ALS Loughrea, Ireland using a highly oxidising digestion with ICP-MS finish (code ME-ICPORE). All techniques were appropriate for the elements being determined. Samples are considered a partial digestion when using an aqua regia digest.
	<i>For geophysical tools, spectrometres, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i>	There was no reliance on determination of analysis by geophysical tools.
	<i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.</i>	Quality Control is monitored through the insertion of one certified reference material (CRM) sample and one blank sample per batch of 20 samples. One pulp duplicate sample is also inserted per batch. The QC results are monitored in real-time, and any failed batches are re-assayed prior to inclusion in the final drill database. Failed batches are determined if a blank sample assays three times the lower detection limit of the element of interest, or if a CRM assays greater than ± 3 standard deviations from the mean, or if two consecutive CRMs assay ± 2 standard deviations from the mean. It is considered that acceptable levels of accuracy and precision have been achieved.
Verification of sampling and assaying	<i>The verification of significant intersections by either independent or alternative company personnel.</i>	There has been no independent logging of significant intersections. Adriatic core was logged by geological staff and verified by the Exploration Manager. Adriatic's drilling has verified the position of historical mineralised intercepts although broader, lower grade intervals are observed relative to historic results. No historical core remains.
	<i>The use of twinned holes.</i>	None of the reported holes are twin holes.
	<i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i>	Primary logging, survey and geotechnical data was entered by the logging geologist into excel sheets per drill hole, and verified and merged with a master acQuire database by the data manager. Data verification includes visual verification by the Database Manager, checking of detailed geological logs against core observations, core photographs and analytical results by the Exploration Manager, and automated data verification using industry standard software. Data is stored on the Virtual Cloud and is regularly backed-up.
	<i>Discuss any adjustment to assay data.</i>	No adjustments were necessary.
Location of data points	<i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i>	Drill collars were surveyed using Total Station to better than 0.05m accuracy. Downhole surveys were related back to the surveyed collar.
	<i>Specification of the grid system used.</i>	UTM WGS Zone 34, Northern Hemisphere



Section 1 Sampling Techniques and Data

(Criteria in this section apply to all succeeding sections.)

Criteria	JORC Code explanation	Commentary
	<i>Quality and adequacy of topographic control.</i>	Topography is derived from LiDAR survey data, collected by Tethyan Resources. It is considered sufficiently accurate for the Company's current exploration activities.
Data spacing and distribution	<i>Data spacing for reporting of Exploration Results.</i>	Drill hole spacing is between 30 and 80 metres and is considered acceptable for reporting of exploration results. The data spacing and distribution is sufficient for this first-stage metallurgical test work, with the 2 test samples representing the currently recognised main mineralisation styles.
	<i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i>	Not applicable as no Mineral Resource or Ore Reserve estimation has been completed.
	<i>Whether sample compositing has been applied.</i>	Sample compositing was not applied for the drill hole reporting.
Orientation of data in relation to geological structure	<i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i>	Holes were drilled at a high angle to mineralised structures. The true thickness of mineralised zones is estimated to vary between 70 to 95% of apparent width.
	<i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material.</i>	It is not considered that the drilling orientation has introduced a sampling bias.
Sample security	<i>The measures taken to ensure sample security.</i>	Chain of Custody of digital data is managed by the Company. Core samples were stored on site in a locked facility and dispatched to the laboratory using a laboratory courier, at which point the laboratory assumed custody of the samples. Samples were examined and photographed on receipt by the laboratory. All sample collection was controlled by digital sample control file(s) and hard-copy ticket books.
Audits or reviews	<i>The results of any audits or reviews of sampling techniques and data.</i>	There have been no audits or reviews of sampling techniques and data.



Section 2: Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section)

Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.	Adriatic Metal's has rights to exploration on four contiguous exploration licences in southwest Serbia, located 250km from Belgrade and collectively referred to as the "Raska Project". Drill holes KZDD-022 to -032, KZDD-035 to -037 and SSDD-003 to -005 which are the subject of this press release are located on exploration licence 2345 "Kizevak" and exploration licence 2346 "Sastavci". Licence 2345 "Kizevak" and 2346 "Sastavci" Exploration licences 2345 "Kizevak" and 2346 "Sastavci" are owned 100% by Ras Metals d.o.o., a private Serbian company. Licence 2345 covers an area of 1.8km² and licence 2346 covers an area of 1.4km². On 01 April 2020, Tethyan Resource Corp announced that it had entered into an arms-length agreement to purchase 100% of EFPP d.o.o. on 31 January 2020. Since the First Closing (May 14th 2020), which consisted of a cash payment of 625,000, EFPP d.o.o has been spun-off into Ras Metals d.o.o. Adriatic Metals Plc currently owns 10% of Ras Metals d.o.o. and at any time within 12 months of First Closing, Adriatic Metals may elect to acquire the remaining 90% of shares of Ras Metals d.o.o. on the Second Closing by: - Paying €1,375,000 to the vendors; - Issuing a total of 664,000 ordinary shares of Adriatic Metals, to be issued in four equal tranches of 166,000 shares, with the first tranche issued on the Second Closing and each additional tranche issued each six months thereafter; and - Paying a deferred cash payment of €500,000 on the two-year anniversary of First Closing. - Issuing 2% NSR for zinc/lead covering Kizevak and Sastavci licenses There are no known native title interests, historical sites, wilderness or national park or environmental settings within the above licence holding. Royalties In addition to the NSR detailed above that comes into effect upon Second Closing, a non-negotiable 5% Net Smelter Return is payable to the Serbian government for metallic raw materials.
	The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area.	Licence 2345 "Kizevak" and 2346 "Sastavci" are both in good standing and are in the first of a three-year exploration period. Both licences expire on 16th October 2022 and may be extended on application for a further six years prior to submission of an application for an Exploitation Licence. There are no known impediments to obtaining a licence to operate in the area.
Exploration done by other parties	Acknowledgment and appraisal of exploration by other parties.	The Raska Project has an extended exploration history, summarised below: 1929-1932: Selection Trust Ltd conducted prospecting and developed underground drives for exploration sampling at Kizevak. 1957-1958: Rudnik Bel Brdo company completed five drill holes at Kizevak, total metreage not known. 1960-1964: Geozavod (Yugoslav state) completed 1:100,000 scale mapping and scout drilling (details not known). 1973-2005: The Geoinstitut (Yugoslav state company) explored the Kizevak, Sastavci and Karadak prospects. At Kizevak, Geoinstitut completed 172 core drill holes totalling 26,727 metres and 29 adits with cross drifts for exploration sampling totalling 7,820m. Open pit mining occurred between 1986 and 2000 and produced 2Mt. At Sastavci, 30 drill holes (7113m) and three adits with cross drives (2626m) were completed leading to small scale open pit mining totalling 40kt of production in 1986. Six core holes (1068m) and 804m of adits and cross drives were completed at Karadak but no mining took place. A foreign resource estimate was reported in 1994 by the Geoinstitut as a combined estimate for the Kizevak, Sastavci and Karadak prospects in the A+B+C1+C2 categories in accordance with Yugoslav GKZ reporting requirements, for 8Mt at 45 g/t silver, 5.06 % zinc and 2.96 % lead. i. "Report on exploration for lead and zinc at the Kizevak-Karakad area in 1994" dated 1995 and authored by Mr B. Rudulović (Izveštaj o istraživanju olova i cinka u području Kiževak - Karadak u 1994. godini).



Section 2: Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section)

Criteria	JORC Code explanation	Commentary
		ii. Yugoslav GKZ mineral resource estimates were always stated as “reserves” and classified according to the A+B+C1+C2 or “alphabetical” classification, which was derived from the Russian system and is still applied throughout many countries in southeast Europe. The reserves had to be approved by the official Commission for Ore Reserves. The A, B, C1 and C2 categories reflect the levels of confidence in the actual tonnage exploited from a reserve, with confidence levels being - 95%, 80%, 70% and 35% respectively. Henley (2004) and others have evaluated the alphabetical classification system with respect to the compliant codes in Canada and Australia, and concluded that A+B is comparable to “measured”, C1 to “indicated” and C2 to “inferred” in internationally acceptable codes for reporting resources. However, these comparisons are only an approximation, and cannot be considered as equivalents. iii. The Company is not treating the foreign estimate as current mineral resources or reserves and considers the foreign estimate to represent an exploration project that requires verification. iv. The foreign estimate is considered to be a useful guide to exploration but the company is not treating the foreign estimate as current mineral resources or ore reserves as defined by the JORC Code. The Company has reviewed and digitised original hard copy drill data, geology logs and assay data, but has not had access to drill core or core photographs; descriptions of sampling, sample preparation or analytical methodology; quality control data; core recovery data; downhole or collar survey data; or sample security information. v. The foreign estimate was based on the results of core drilling and underground sampling completed by the Geoinstitut between 1973-1994. It was estimated using the polygonal method assuming an open pit mining scenario and prevailing metal prices at the time. vi. No more recent estimates or data relevant to the foreign estimate are available to the Company except for the results of KSEDD001 to KSEDD014 drilled by Tethyan Resources during 2018-2019. vii. To verify the foreign estimate as mineral resources in accordance with Appendix 5A (JORC Code) the Company intends to perform geological mapping, geophysical surveys and core drilling. An initial 3000m of core drilling is planned to verify the presence and grade of mineralisation, and the results will be used to plan additional exploration programs to facilitate future mineral resource estimation in accordance with the JORC Code, if warranted. viii. The exploration work is proposed over a 12 month period commencing on the First Closing and enduring to the Second Closing, at which point the Company will elect whether or not to proceed with the option agreement with EFPP. The Company intends to fund this work using current cash resources. ix. The foreign estimate is not reported in accordance with the JORC Code. A competent person has not done sufficient work to classify the foreign estimate as mineral resources or ore reserves in accordance with the JORC Code. It is uncertain that following evaluation and/or further exploration that the foreign estimate will be able to be reported as mineral resources or ore reserves in accordance with the JORC Code. • 2005-2008: no work known to have occurred at the Kizevak-Sastavci prospects. • 2004-2007: Phelps Dodge explored the Rudnica copper-gold porphyry including seven core holes for at least 1310 m. • 2007-2009: Euromax drilled one hole at the Rudnica copper-gold porphyry • 2009-2015: Farmakom d.o.o. a private Serbian company explored the Kizevak, Sastavci and Rudnica prospects licences. Work completed not known. • 2016-2018: Licence 2176 “Kremice” was granted to Taor do.o., a private Serbian company, who completed a desk-based remote sensing study prior to being acquired by Tethyan Resource Corp on 03.07.2018. • 2016: Licence 2150 “Raska” was granted to Deep Research d.o.o. • 2019: Licence 2345 “Kizevak” and 2346 “Sastavci” were granted to EFPP d.o.o.
Geology	<i>Deposit type, geological setting and style of mineralisation.</i>	Mineralisation in the Raska Project is hosted in andesite volcanics and volcanoclastics, intruded by coeval diorite dykes and post-mineral diorite and quartz latite dykes. The volcanic sequence unconformably overlies a serpentinised ophiolitic melange. A massive, grey to red limestone unit is juxtaposed against the andesite package to the south of the Kizevak prospect.



Section 2: Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section)

Criteria	JORC Code explanation	Commentary
		The Kizevak, Sastavci and Karadak deposits are intermediate sulphidation, polymetallic (Ag-Pb-Zn) epithermal vein arrays hosted in an extensional fault setting. Kizevak occurs over a total strike length of >1.3km. Approximately 200m of the known strike length is within exploration licence 2176 "Kremice" which is the southeast extension of the past producing Kizevak open pit mine. Sastavci mineralisation has been defined by historical drilling over a strike length of 1.2km within a 250m wide zone, which contains several sub-parallel veins and lenses. Karadak has been defined by historical drilling over a strike length of 400m within one to four sub-parallel veins. Mineralisation comprises <1 to >5m thick, massive to semi-massive sulphide veins with broad (10-40m thick) zones of crackle breccia and stockwork veins in the hanging walls. All veins are composed of galena-sphalerite-pyrite-bourbonite-chalcopryrite-tetrahedrite with intergrowths of Pb-As sulfosalts and quartz-carbonate (rhodochrosite) gangue. The veins are occasionally milled and brecciated as a result of fault reactivation, which forms clay rich, unconsolidated mineralised zones. Mineralisation is associated with an intense pyrite-clay (illite-smectite), magnetite destructive alteration. The Rudnica and Kremice Porphyry prospects are copper-gold porphyry deposits which display stockwork A, B and C-type veins composed of variable quartz, pyrite, chalcopryrite and magnetite. Stockwork veins are dominantly hosted within an early diorite porphyry intrusion (P10), an intermediate diorite dyke (P20) and country rocks (serpentinite and andesite). A late diorite dyke (P30) crosscuts mineralisation. At Rudnica, a 50 to 80m thick, gold-mineralised, copper-poor, leached and oxidised cap overlies a 10-50 m thick supergene copper enrichment zone (chalcocite blanket), which overprints the deeper hypogene mineralisation. Mineralisation has been defined over 400 by 250 m, to a depth of 550m below surface, and is open in most directions. At Kremice, mapping has defined an area of 450 by 450m with stockwork A and B type quartz-pyrite ± magnetite veins within a 1200 by 600 m soil anomaly.
Drill hole information	<i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i> - o easting and northing of the drill hole collar - o elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar - o dip and azimuth of the hole - o downhole length and interception depth - o hole length. <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i>	Drilling data for the reported drill holes is included in Tables 1-3 of Appendix 1 in this document.
Data aggregation methods	<i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (e.g. cutting of high grades) and cut-off grades are usually Material and should be stated.</i>	Significant intercepts were truncated by applying a lower cut-off grade of 1% Pb+Zn (see below assumptions for ZnEq calculation) and maximum internal dilution of 5m. No top-cutting was applied. Significant intercepts were reported as weighted averages.
	<i>Where aggregate intercepts incorporate short lengths of high-grade results and longer lengths of low-grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i>	Short lengths of high-grade results were defined as >5% Pb+Zn and maximum internal dilution of 5m. Results are shown in Table 1 of the main reporting document.



Section 2: Reporting of Exploration Results

(Criteria listed in the preceding section also apply to this section)

Criteria	JORC Code explanation	Commentary
	<i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i>	ZnEq grades are based on the following metal prices: \$1850/oz gold, \$22/oz silver, \$1900/t lead, \$2350/t zinc, and the following metal recoveries were used on the basis of preliminary testing inclusive of smelter charges and payabilities: 75% silver, 85% lead and 85 % zinc. Gold recovery of 80% was estimated as there have been no gold recovery tests conducted to date. The zinc equivalent calculation is as follows: $ZnEq = 100 * ((Au \text{ grade g/t} * Au \text{ recovery \%} * Au \text{ price \$ /g}) + (Ag \text{ grade g/t} * Ag \text{ recovery \%} * Ag \text{ price \$ /g}) + ((Pb \text{ grade \%} * Pb \text{ recovery \%} * Pb \text{ price \$ /t}) / 100) + ((Zn \text{ grade \%} * Zn \text{ recovery \%} * Zn \text{ price \$ /t}) / 100)) / Zn \text{ price \$ /t})$.
Relationship between mineralisation widths and intercept lengths	<i>These relationships are particularly important in the reporting of Exploration Results.</i> <i>If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.</i> <i>If it is not known and only the downhole lengths are reported, there should be a clear statement to this effect (e.g. 'downhole length, true width not known').</i>	Only downhole lengths are reported, true widths are not known. True widths are estimated as between 75 and 90% of the apparent width.
Diagrams	<i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported. These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i>	Relevant maps and diagrams are included in the body of the report. Metallurgical test work results being reported do not require maps and diagrams.
Balanced reporting	<i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high-grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i>	All assay tables for all reported holes are included in the main reporting document.
Other substantive exploration data	<i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density; groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i>	No substantive exploration data not already mentioned in the announcement or in this table have been used.
Further work	<i>The nature and scale of planned further work (e.g. tests for lateral extensions or depth extensions or large-scale step-out drilling).</i>	Further drilling will be undertaken for exploration along strike and down dip, the nature of which is dependent on exploration success and funding. Further drilling will be undertaken for geotechnical and metallurgical purposes, to include locked cycle tests, bulk samples and variability testing
	<i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i>	Diagrams have been included in the body of this announcement.